

18 December 2024

## Aurum hits 277 g/t gold at Boundiali BM Target 3

Aurum Resources (ASX: AUE) reports exceptional high-grade gold intercepts from its Boundiali Gold Project in Côte d'Ivoire, including a project-best intercept of **1.19m at 277.54 g/t Au**.

### Highlights

- Exploration diamond drilling (38 holes for 10,090m) targeting multiple prospects on the Boundiali **BM** tenement returns shallow, wide and high-grade gold hits<sup>1</sup> including:
  - **1.19m @ 277.54 g/t Au** from 31m (MBDD118)
  - **1m @ 73.77 g/t Au** from 38m & **12m @ 2.14 g/t Au** from 43m & **6m @ 4.46 g/t Au** from 56m & **15m @ 1.17 g/t Au** from 132m (MBDD112)
  - **20m @ 1.61 g/t Au** from 60m & **5m @ 2.76 g/t Au** from 82m & **5m @ 3.12 g/t Au** from 91m & **6m @ 3.81 g/t Au** from 98m (MBDD114)
- Exploration diamond drilling (38 holes for 11,784m) targeting multiple prospects on the Boundiali **BD** tenement returns shallow, wide and high-grade gold hits<sup>2</sup> including:
  - **0.96m @ 75.02 g/t Au** from 269.04m & **5m @ 6.55 g/t Au** from 481m inc. **1m @ 31.94 g/t Au** & **21.39m @ 1.07 g/t Au** from 489m inc. **4m @ 3.33 g/t Au** (DSDD0124)
  - **33m @ 0.84 g/t Au** from 341m inc. **6m @ 2.03 g/t Au** & **13.88m @ 1.45 g/t Au** from 377m inc. **1m @ 14.79 g/t Au** (DSDD0123A)
  - **15.78m @ 1.70 g/t Au** from 121.22m inc. **6m @ 2.99 g/t Au** (DSDD0110)
- **These results demonstrate the emerging potential of the Boundiali project, with mineralisation remaining open along strike and at depth.**
- Aurum's six self-owned diamond rigs **continue to drill** at Boundiali and will complete more than **50,000m** in CY2024 and **100,000m** is targeted in CY2025
- **Excellent results** reported from **BD metallurgical** testwork with **+95% gold recoveries** (gravity + leaching)<sup>3</sup>
- **Inaugural Mineral Resource Estimate** for Boundiali Gold Project on track before end **CY2024**
- Aurum's takeover of Mako Gold (ASX: MXG)<sup>4</sup> **declared unconditional** – the merged company to achieve greater scale and market presence, with a stronger platform for future growth and success
- **Aurum is well-funded<sup>5</sup> (~\$23M cash at bank)** for continued aggressive exploration.

**Aurum's Managing Director Dr. Caigen Wang** said: *"These latest results include a **project best high-grade gold result** for Boundiali with hole MBDD118 hitting **1.19 m @ 277.54 g/t Au from 31m**. This discovery, made in shallow oxide material, is particularly exciting as it comes from one of the first holes drilled in a newly identified zone with three parallel structures NW of our drilling at BM Target 3.*

*These data are now with our resource modelling team who are on track to deliver the inaugural Boundiali Mineral Resource estimate before year-end. This estimate will incorporate results from the BD, BM, and BST prospects.*

<sup>1</sup> Refer to Table 1 for collar information and Table 3 for assay results for the BM drilling

<sup>2</sup> Refer to Table 2 for collar information and Table 4 for assay results for the BD drilling

<sup>3</sup> ASX 4 December 2024; Over 95% gold recovery from the Boundiali Gold Project

<sup>4</sup> The full terms of the bid are set out in the Bidder Statement lodged with ASX and ASIC on 30 October 2024 (declared unconditional on 22 November 2024)

<sup>5</sup> ASX 6 December 2024; AUE receives firm commitments for A\$10 million placement



*Importantly, numerous gold-in-soil anomalies remain untested, offering significant potential for resource growth in 2025 and beyond.*

*Regarding our takeover offer for Mako Gold, we are now past the 70% ownership threshold and have control of the Mako board. This puts us in a strong position to complete the compulsory acquisition process. We encourage remaining Mako Gold shareholders to accept our offer promptly before the offer closes at 7pm AEST on 31 January 2025."*

### **BM - Latest Drill Results**

Aurum reports results for 38 holes for 10,089.90m of diamond core drilled at its BM tenement including at **BM Target 1** (29 holes for 8,389.90m), **BM Target 3** (eight (8) holes for 1,530m) and **BM Target 4** (one hole for 170m), part of an expanded drill program at **BM** where Aurum holds an 80% project interest<sup>6</sup>.

Best results for the new holes<sup>7</sup> include:

#### BM Target 1

- **0.93m @ 38.76 g/t Au** from 56.33m (MBDD098)
- **1m @ 32.12 g/t Au** from 117m (MBDD092)
- **5m @ 2.72 g/t Au** from 48m inc. **2m @ 6.28 g/t Au** (MBDD111)

#### BM Target 3

- **1.19m @ 277.54 g/t Au** from 31m (MBDD118)
- **1m @ 73.77 g/t Au** from 38m & **12m @ 2.14 g/t Au** from 43m & **6m @ 4.46 g/t Au** from 56m & **15m @ 1.17 g/t Au** from 132m (MBDD112)
- **20m @ 1.61 g/t Au** from 60m & **5m @ 2.76 g/t Au** from 82m & **5m @ 3.12 g/t Au** from 91m & **6m @ 3.81 g/t Au** from 98m (MBDD114)

#### BM Target 4

- **2m @ 0.48 g/t Au** from 25m (MBDD055)

These new results are in addition to diamond holes drilled and reported<sup>8</sup> by Aurum at **BM**, which included:

- **11.46m @ 6.67 g/t Au** from 162.54m incl. **1.46m @ 45.04 g/t Au** (MBDD049)
- **45m @ 0.93 g/t Au** from 78m incl. **8m @ 1.18 g/t Au** from 78m & **25m @ 1.15 g/t Au** from 98m (MBDD0045)
- **17.31m @ 5.90 g/t Au** from 273.69m inc. **6m @ 16.07 g/t Au** (MBDD081)
- **29m @ 1.55 g/t Au** from 178m inc. **13m @ 2.19 g/t Au** (MBDD086).
- **1m @ 35.86 g/t Au** from 82m & **4.25m @ 3.75 g/t Au** from 120m (MBDD070)
- **16m @ 1.24 g/t Au** from 117m incl. **6m @ 2.44 g/t Au** (MBDD0010)
- **7.39m @ 1.94 g/t Au** from 139.34m incl. **5.35m @ 2.53 g/t Au** (MBDD017)
- **16.3m @ 1.02 g/t Au** from 86.7m incl. **8m @ 1.71 g/t Au** (MBDD019)
- **16.64m @ 1.45 g/t Au** from 56.26m incl. **10.40m @ 2.11 g/t Au** (MBDD007)
- **5m @ 4.73 g/t Au** from 53.5m incl. **1.10m @ 20.35 g/t Au** (MBDD004)

<sup>6</sup> Refer to About Aurum's Boundiali Gold Project

<sup>7</sup> Refer to Table 1 for collar information and Table 3 for assay results for the BM drilling

<sup>8</sup> Refer to Compliance Statement for details on previous reporting on ASX

Aurum's geologists used information from previous drilling and mapped the prospects, which include some large artisanal pits. **BM Target 3 NW** was identified from field work and has reported the project best intercept (**1.19m @ 277.54 g/t Au** from 31m, MBDD118). True widths for these shallow wide high-grade gold intercepts are estimated at about 70% - 80% of reported downhole lengths.

Details of drill collar location and assay results for the new drilling at **BM** can be found in Table 1 and Table 2 respectively. Plans showing location of the Boundiali Gold Project and the assay results are presented in (general locations in Figure 1 to Figure 2 and detailed plans in Figure 3 to Figure 4). A cross section showing the latest drill results is presented in Figure 7. Gold mineralisation remains open along strike and at depth on all prospects, with drilling ongoing and Aurum planning further work to follow up these initial results.

### BD - Latest Drill Results

Aurum reports results for 38 holes for 10,089.90m of diamond core drilled on the **BD Tenement** which included at **BD Target 1** (29 holes for 8,389.90m), **BD Target 2** (eight (8) holes for 1,530m), where Aurum holds an 80% project interest<sup>9</sup>.

Best results for these new holes<sup>10</sup> include:

#### BD Target 1

- **0.96m @ 75.02 g/t Au** from 269.04m & **5m @ 6.55 g/t Au** from 481m inc. **1m @ 31.94 g/t Au & 21.39m @ 1.07 g/t Au** from 489m inc. **4m @ 3.33 g/t Au** (DSDD0124)
- **10m @ 2.43 g/t Au** from 473m inc. **4m @ 6.01 g/t Au & 15m @ 0.69 g/t Au** from 487m inc. **2m @ 1.23 g/t Au** (DSDD0121)
- **6m @ 1.26 g/t Au** from 257m & **22m @ 0.84 g/t Au** from 267m inc. **5m @ 1.48 g/t Au & 15m @ 1.54 g/t Au** from 470m inc. **8m @ 2.64 g/t Au** (DSDD0127)

#### BD Target 2

- **33m @ 0.84 g/t Au** from 341m inc. **6m @ 2.03 g/t Au & 13.88 m @ 1.45 g/t Au** from 377m inc. **1m @ 14.79 g/t Au** (DSDD0123A)
- **1m @ 12.26 g/t Au from 109m & 15.78m @ 1.70 g/t Au** from 121.22m inc. **6m @ 2.99 g/t Au** (DSDD0110)

These new results are in addition to diamond holes drilled and reported<sup>11</sup> by Aurum at **BD**, which included:

- **73m @ 2.15g/t Au** from 172m inc. **4m @ 18.63g/t Au** (DSDD0012)
- **90m @ 1.16 g/t Au** from 143m inc. **51m @ 1.04 g/t Au** and **35m @ 1.47 g/t Au** (DSDD0050)
- **59m @ 1.42 g/t Au** from 68m inc. **13m @ 3.92 g/t Au** (DSDD0010)
- **36m @ 2.53 g/t Au** from 104m inc. **16m @ 5.03 g/t Au** (DSDD0011)
- **4m @ 22.35 g/t Au** from 226m (173m below surface) (DSDD0004)
- **12.22m @ 14.56 g/t Au** from 275m inc. **1m @ 163.42 g/t Au** (DSDD0051)
- **69m @ 1.05 g/t Au** from 195m inc. **12m @ 2.28 g/t Au** (DSDD0060A)

<sup>9</sup> Refer to About Aurum's Boundiali Gold Project

<sup>10</sup> Refer to Table 1 for collar information and Table 3 for assay results for the BM drilling

<sup>11</sup> Refer to Compliance Statement for details on previous reporting on ASX



- **40m @ 1.03 g/t Au** from 136m inc. **5m @ 1.70 g/t Au** (DSDD0076)

True widths for these shallow wide high-grade gold intercepts are estimated at about 70% - 80% of reported downhole lengths.

Details of drill collar location and assay results for the new drilling at BD can be found in Table 2 and Table 4 respectively.

Plans showing location of the Boundiali Gold Project and the assay results are presented in (general locations in Figure 1 to Figure 2 and detailed plans in Figure 5 to Figure 6). A cross section showing the latest drill results is presented in Figure 8 to Figure 9.

Gold mineralisation remains open along strike and at depth on all prospects, with drilling ongoing and Aurum planning further work to follow up these initial results.

### **Next steps**

Aurum will continue its high-tempo gold exploration drilling at the Boundiali Gold Project and exploration drilling on the early-stage **BM** tenement which is designed to test for potential new discoveries. Scout and step-back diamond drilling at the **BD** tenement will continue, aiming to delineate known gold zones and identify new targets.

With six diamond drill rigs in operation, Aurum expects to drill more than 50,000m of diamond core at Boundiali in CY2024. Assays from this drilling are being incorporated into the inaugural Mineral Resource Estimate for the Boundiali Gold Project, which is expected by the end of CY2024.

Aurum is well-funded to execute these exploration plans with ~\$23M cash at bank and remains confident in the potential of the Boundiali Gold Project to deliver significant value for shareholders.

### **Aurum's takeover bid for Make Gold Limited**

On 16 October 2024, Aurum launched a takeover bid for Mako Gold Limited (ASX: MKG) with the following highlights:

- Mako Gold Limited (MKG) and Aurum Resources Limited (AUE) signed a Bid Implementation Agreement (BIA), for an agreed merger pursuant to which Aurum proposes to acquire 100% of the issued shares in Mako and 100% of two classes of unlisted options by way of an off-market takeover bid (Proposed Merger)
- Proposed Merger will create an emerging exploration and development gold business in West Africa to advance the flagship Napié and Boundiali Gold Projects in northern Côte d'Ivoire
- Aurum to offer:
  - 1 Aurum share for every 25.1 Mako shares, representing an offer price of \$0.018 per Mako share (Share Offer)
  - 1 Aurum share for every 170 Class A Options
  - 1 Aurum share for every 248 Class B Options
- Offer represents a 112% premium for Mako shareholders based on the 30-day VWAP of A\$0.00855 (Based on Aurum's 5-day volume weighted average price of A\$0.455 per share as of 11 October 2024, being the last trading day prior to announcement of the Proposed Merger)



- Mako shareholders will own 20.5% of the merged entity under the Share Offer while Aurum shareholders will own the remaining 79.5%
- Mako Directors **unanimously recommend** that, in the absence of a superior proposal, all shareholders and option holders accept Aurum's offers
- The combined group will be pursuing its growth strategy from a position of greater market scale, underpinned by a strong cash balance and lower consolidated cost base.

On 22 November 2024, Aurum declared its takeover offer for all Mako shares unconditional and the offer will close at 7.00pm (Sydney time) on 31 January 2025 (unless extended).

In preparation for a successful conclusion of the takeover, Aurum purchased two new diamond drill rigs and 30,000m of drilling consumables and spare parts, which were shipped from China on 10 November 2024 and are expected to arrive in Côte d'Ivoire on 19 December 2024.

This update has been authorised by the Board of Aurum Resources Limited.

ENDS

#### **FORWARD-LOOKING STATEMENTS**

*This ASX release contains forward-looking statements about Aurum Resources Limited's exploration activities, drilling programs, and potential Mineral Resource Estimate at the Boundiali Gold Project. These statements are based on current expectations and are subject to risks and uncertainties inherent in mineral exploration and mining. Factors that could cause actual results to differ materially include exploration risks, drilling results, resource estimation, gold prices, operational risks, regulatory changes, and broader economic conditions. Investors should not place undue reliance on these forward-looking statements.*

#### **COMPETENT PERSONS STATEMENT**

*The information in this release that relates to Exploration Targets and Exploration Results is based on information compiled by Mr Mark Strizek, a Competent Person who is a Member of The Australasian Institute of Mining and Metallurgy. Mr Strizek has been a non-executive Director of the Company since 1 February 2024 and joined as an executive Director on 1 June 2024. Mr Strizek has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity being undertaken to qualify as a Competent Person as defined in the 2012 edition of the "Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves". Mr Strizek consents to the inclusion in the announcement of the matters based on his information in the form and context in which it appears. Additionally, Mr Strizek confirms that the entity is not aware of any new information or data that materially affects the information contained in the ASX releases referred to in this presentation.*

#### **COMPLIANCE STATEMENT**

*This report contains information extracted from ASX market announcements reported in accordance with the 2012 edition of the "Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves" ("2012 JORC Code") and available for viewing at [www.asx.com](http://www.asx.com) and includes results reported previously and published on ASX platform:*

- 13 Dec 2024, Change Of Directors and Addition of Joint Company Secretary (ASX:AUE & ASX:MKG)*
- 6 Dec 2024, AUE receives firm commitments for A\$10 million placement (ASX:AUE)*
- 04 Dec 2024, Clarification Ann - Over 95% gold recovery from Boundiali (ASX:AUE)*
- 03 Dec 2024, 3 Dec 2024 Mako Takeover Update (ASX:AUE)*
- 02 Dec 2024, Over 95% gold recovery from the Boundiali Gold Project (ASX:AUE)*
- 29 Nov 2024, Aurum earns 80% interest in Boundiali BM tenement (ASX:AUE)*
- 28 Nov 2024, AUE appoints Mr. Steve Zaninovich as Non-Executive Director (ASX:AUE)*
- 25 Nov 2024, Aurum hits 17.31m at 5.90 g/t gold at Boundiali BM Target 1 (ASX:AUE)*



22 Nov 2024, AUE Declares Takeover Offer for all MKG Shares Unconditional (ASX:AUE)  
15 Nov 2024, Supplementary Bidders Statement (ASX:AUE)  
11 Nov 2024, Aurum hits 36 g/t gold at BM T1 of 2.5km strike (ASX:AUE)  
30 Oct 2024, Bidders Statement (ASX:AUE)  
16 Oct 2024, Recommended Takeover of Mako Gold By Aurum Resources (ASX:AUE)  
09 Sep 2024, Aurum earns 51% interest in Boundiali BM tenement (ASX:AUE)  
05 Sep 2024, AUE hits 40m at 1.03 g/t gold at Boundiali BD Target 1 (ASX:AUE)  
03 Sep 2024, Boundiali South Exploration Licence Renewed (ASX:AUE)  
07 Aug 2024, Aurum to advance met studies for Boundiali Gold Project (ASX:AUE)  
22 July 2024, Prelim metallurgical tests deliver up to 99% gold recovery (ASX:AUE)  
17 June 2024, Aurum hits 69m at 1.05 g/t gold at Boundiali BD Target 1 (ASX:AUE)  
28 May 2024, AUE hits 163 g/t gold in 12m @ 14.56 g/t gold at BD Target 1 (ASX:AUE)  
24 May 2024, Aurum hits 74m @ 1.0 g/t gold at Boundiali BD Target 2 (ASX:AUE)  
15 May 2024, Aurum expands Boundiali Gold Project footprint (ASX:AUE)  
10 May 2024, AUE hits 90m @ 1.16 g/t gold at Boundiali BD Target 1 (ASX:AUE)  
01 May 2024, Aurum Appoints Country Manager in Cote d'Ivoire (ASX:AUE)  
23 April 2024, AUE drilling hits up to 45 g/t gold at Boundiali BD Target 2 (ASX:AUE)  
19 March 2024, AUE signs binding term sheet for 100% of Boundiali South (ASX:AUE)  
12 March 2024, AUE hits 73m at 2.15g/t incl 1m at 72g/t gold at Boundiali (ASX:AUE)  
01 March 2024, Aurum hits 4m at 22 g/t gold in Boundiali diamond drilling (ASX:AUE)  
22 January 2024, Aurum hits shallow, wide gold intercepts at Boundiali, Côte d'Ivoire (ASX: AUE)  
21 December 2023, Rapid Drilling at Boundiali Gold Project (ASX:AUE)  
21 November 2023, AUE Acquisition Presentation (ASX:AUE)  
21 June 2021, Notice of General Meeting/Proxy Form (MSR.ASX)  
21 May 2021, PlusOr to Acquire 6194 sq kms Ground Position in Cote d'Ivoire (MSR.ASX)  
22 August 2019, Boundiali RC Drill Results Continue to Impress (PDI.ASX)  
15 July 2019, RC, Trench Results Grow Boundiali Potential In Cote D'Ivoire (PDI.ASX)  
27 May 2019, New Drill Results Strengthen Boundiali Project Cote D'Ivoire (PDI.ASX)  
16 January 2019, PDI-Toro JV Sharpens Focus with Major Drilling Program (PDI.ASX)  
26 November 2018, Boundiali North - Large Coherent Gold Anomalies in 14km Zone (PDI.ASX)

*The Company confirms that it is not aware of any new information or data that materially affects the information included in the previous announcements.*




Figure 1: Location of Aurum's Boundiali Gold Project in Côte d'Ivoire




Figure 2: Aurum's Boundiali Gold Project






Figure 3: BM tenement plan view showing new significant drilling results<sup>12</sup> (yellow) at BM Target 1

<sup>12</sup> Only showing new results having gold gram metres greater than 5




Figure 4: BM tenement plan view showing new significant drilling results (yellow) at BM Target 3




Figure 5: BD tenement plan view showing new significant drilling results<sup>13</sup> (yellow) at BD Target 1




Figure 6: BD tenement plan view showing new significant drilling results (yellow) at BD Target 2

<sup>13</sup> Only showing new results having gold gram metres greater than 5




Figure 7: Oblique Cross Section looking northeast (+/-50m) showing new drill results MBDD116 – BM Target 3




Figure 8: Cross Section looking north (+/-25m) showing new drill results DSDD0124 – BD Target 1




Figure 9: Cross Section looking north (+/-50m) showing new drill results DSDD0123A – BD Target 2

**Table 1: Drill Collar Information BM**

Hole ID	UTM East	UTM North	Depth (m)	Dip deg	Azi deg	Prospect	Type
MBDD071	796,665	1,093,749	427.50	-58	290	BM Target 1	D
MBDD073	796,078	1,092,438	122.50	-55	290	BM Target 1	D
MBDD082	796,273	1,092,884	207.00	-60	290	BM Target 1	D
MBDD083	796,251	1,092,734	209.00	-60	290	BM Target 1	D
MBDD084	796,302	1,092,779	301.00	-60	290	BM Target 1	D
MBDD087	796,322	1,092,864	301.50	-60	290	BM Target 1	D
MBDD088	796,450	1,093,662	179.50	-60	290	BM Target 1	D
MBDD089A	796,241	1,092,486	215.50	-60	290	BM Target 1	D
MBDD091	796,064	1,092,317	214.50	-60	290	BM Target 1	D
MBDD092	796,609	1,093,929	203.30	-60	290	BM Target 1	D
MBDD094	796,091	1,092,191	210.50	-60	290	BM Target 1	D
MBDD095	796,442	1,093,242	223.50	-60	290	BM Target 1	D
MBDD096	796,677	1,094,222	265.50	-60	290	BM Target 1	D
MBDD097	796,655	1,093,914	284.00	-60	290	BM Target 1	D
MBDD098	796,046	1,092,551	213.50	-60	290	BM Target 1	D
MBDD099A	796,492	1,093,225	311.60	-60	290	BM Target 1	D
MBDD100	796,484	1,093,158	356.00	-60	290	BM Target 1	D
MBDD102	796,761	1,094,402	258.50	-60	290	BM Target 1	D
MBDD103	796,836	1,094,591	262.50	-60	290	BM Target 1	D
MBDD104	796,618	1,094,030	428.00	-65	290	BM Target 1	D
MBDD105	796,839	1,094,481	254.50	-60	290	BM Target 1	D
MBDD106	796,728	1,094,311	253.00	-60	290	BM Target 1	D
MBDD107	796,802	1,094,057	637.50	-60	290	BM Target 1	D
MBDD108	796,561	1,093,842	266.00	-60	290	BM Target 1	D
MBDD109	795,095	1,078,690	190.50	-50	105	BM Target 1	D
MBDD110	796,610	1,093,823	374.00	-60	290	BM Target 1	D
MBDD111	796,320	1,092,567	406.50	-65	290	BM Target 1	D
MBDD113	796,291	1,092,462	425.00	-65	290	BM Target 1	D
MBDD116	796,577	1,093,309	388.00	-65	290	BM Target 1	D
<b>29 Holes</b>			<b>8,389.90</b>			<b>BM Target 1</b>	
Hole ID	UTM East	UTM North	Depth (m)	Dip deg	Azi deg	Prospect	Type
MBDD069	794,980	1,078,234	176.50	-50	15	BM Target 3	
MBDD085	795,007	1,078,312	219.00	-50	15	BM Target 3	
MBDD093	795,042	1,078,099	215.00	-60	105	BM Target 3	
MBDD101A	795,121	1,078,512	195.00	-50	105	BM Target 3	



Hole ID	UTM East	UTM North	Depth (m)	Dip deg	Azi deg	Prospect	Type
MBDD112	795,199	1,078,940	216.00	-50	105	BM Target 3	
MBDD114	795,225	1,079,118	211.50	-50	105	BM Target 3	
MBDD115	794,877	1,082,122	136.50	-55	300	BM Target 3	
MBDD118	793,961	1,082,269	160.50	-55	290	BM Target 3	
<b>8 Holes</b>			<b>1,530.00</b>			<b>BM Target 3</b>	
Hole ID	UTM East	UTM North	Depth (m)	Dip deg	Azi deg	Prospect	Type
MBDD055	795,051	1,061,109	170.00	-55	270	BM Target 4	
<b>All</b>			Depth (m)			Total BM	
<b>38 holes</b>			<b>10,089.90</b>				



**Table 2: Drill Collar Information BD Target**

Hole ID	UTM East	UTM North	Depth (m)	Dip deg	Azi deg	Prospect	Type
DSDD0094	788,196	1,054,882	180.00	-60	270	BD Target 1	D
DSDD0097	787,351	1,055,686	188.50	-60	300	BD Target 1	D
DSDD0099A	787,548	1,055,568	276.50	-55	300	BD Target 1	D
DSDD0102	787,598	1,055,878	166.50	-60	300	BD Target 1	D
DSDD0103	787,613	1,055,691	252.00	-60	300	BD Target 1	D
DSDD0106	787,609	1,055,539	252.00	-60	300	BD Target 1	D
DSDD0107	787,679	1,055,823	276.00	-60	300	BD Target 1	D
DSDD0108	787,725	1,055,915	277.00	-60	300	BD Target 1	D
DSDD0111	788,023	1,052,880	281.50	-55	270	BD Target 1	D
DSDD0112	787,804	1,055,978	276.00	-60	300	BD Target 1	D
DSDD0114	787,998	1,052,614	252.50	-60	270	BD Target 1	D
DSDD0116	787,483	1,055,454	276.00	-60	300	BD Target 1	D
DSDD0118	787,926	1,052,464	250.50	-60	270	BD Target 1	D
DSDD0121	787,990	1,054,266	561.50	-67	270	BD Target 1	D
DSDD0122	787,855	1,052,234	213.00	-55	270	BD Target 1	D
DSDD0124	787,970	1,054,421	538.50	-67	270	BD Target 1	D
DSDD0127	787,965	1,054,365	547.50	-67	270	BD Target 1	D
DSDD0131	788,027	1,054,493	608.50	-67	270	BD Target 1	D
DSDD0135	788,878	1,059,432	302.00	-50	270	BD Target 1	D
<b>18 Holes</b>			<b>5,674.00</b>			<b>BD Target 1</b>	
Hole ID	UTM East	UTM North	Depth (m)	Dip deg	Azi deg	Prospect	Type
DSDD0061	789,186	1,060,255	301.50	-55	270	BD Target 2	DD
DSDD0088B	789,373	1,059,529	300.75	-50	270	BD Target 2	DD
DSDD0092	789,223	1,059,751	202.50	-50	270	BD Target 2	DD
DSDD0095	789,380	1,059,749	304.00	-50	270	BD Target 2	DD
DSDD0098	789,424	1,059,627	373.00	-55	270	BD Target 2	DD
DSDD0100	789,234	1,059,298	259.00	-50	270	BD Target 2	DD
DSDD0101	789,253	1,059,830	301.00	-50	270	BD Target 2	DD
DSDD0104	789,391	1,059,297	310.00	-50	270	BD Target 2	DD
DSDD0105	789,386	1,059,827	300.00	-50	270	BD Target 2	DD
DSDD0109	789,550	1,059,824	301.00	-50	270	BD Target 2	DD
DSDD0110	789,211	1,059,199	308.00	-50	270	BD Target 2	DD
DSDD0113	789,443	1,059,975	302.00	-50	270	BD Target 2	DD
DSDD0115	789,351	1,059,202	302.50	-50	270	BD Target 2	DD
DSDD0117	789,290	1,060,019	301.00	-50	270	BD Target 2	DD



Hole ID	UTM East	UTM North	Depth (m)	Dip deg	Azi deg	Prospect	Type
DSDD0119	789,503	1,060,049	302.00	-50	270	BD Target 2	DD
DSDD0120	788,828	1,059,367	302.50	-50	270	BD Target 2	DD
DSDD0123A	789,055	1,059,628	428.50	-60	87	BD Target 2	DD
DSDD0129	789,038	1,059,445	308.00	-50	0	BD Target 2	DD
DSDD0132	788,889	1,059,439	300.50	-50	325	BD Target 2	DD
<b>20 holes</b>			<b>6,109.75</b>			<b>BD Target 2</b>	
<b>All</b>			<b>Depth (m)</b>			<b>Total BD</b>	
<b>38 holes</b>			<b>11,783.75</b>				

**Table 3: Significant assay results for holes being reported for BM<sup>14</sup>**

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
MBDD055	25.00	26.00	1.00	0.25	2 m @ 0.48 g/t Au	1.0	
MBDD055	26.00	27.00	1.00	0.71			
MBDD055	96.00	97.00	1.00	0.38	1 m @ 0.38 g/t Au	0.4	
MBDD069					NSI		
MBDD071	339.00	340.00	1.00	0.44	1 m @ 0.44 g/t Au	0.4	
MBDD071	345.00	346.00	1.00	<b>5.43</b>	<b>2 m @ 2.94 g/t Au</b>	<b>5.9</b>	<b>1 m @ 5.43 g/t Au</b>
MBDD071	346.00	347.00	1.00	0.44			
MBDD071	409.00	410.00	1.00	0.89	1 m @ 0.89 g/t Au	0.9	
MBDD071	416.00	417.00	1.00	0.70	1 m @ 0.70 g/t Au	0.7	
MBDD073	60.57	61.50	0.93	0.29	0.93 m @ 0.29 g/t Au	0.3	
MBDD082	123.00	124.00	1.00	0.27	1 m @ 0.27 g/t Au	0.3	
MBDD082	141.51	143.00	1.49	<b>1.77</b>	<b>2.49 m @ 1.14 g/t Au</b>	2.8	<b>1.49 m @ 1.77 g/t Au</b>
MBDD082	143.00	144.00	1.00	0.20			
MBDD083					NSI		
MBDD084	254.00	255.00	1.00	0.28	1 m @ 0.28 g/t Au	0.3	
MBDD084	269.00	270.00	1.00	0.41	1 m @ 0.41 g/t Au	0.4	
MBDD084	287.00	288.00	1.00	0.82	1 m @ 0.82 g/t Au	0.8	
MBDD085					NSI		
MBDD087	180.00	181.00	1.00	0.69	5 m @ 0.44 g/t Au	2.2	
MBDD087	181.00	182.00	1.00	0.05			
MBDD087	182.00	183.00	1.00	0.01			
MBDD087	183.00	184.00	1.00	0.79			
MBDD087	184.00	185.00	1.00	0.68			
MBDD087	195.00	196.00	1.00	0.20	1 m @ 0.20 g/t Au	0.2	
MBDD087	206.00	207.00	1.00	0.41	2 m @ 0.59 g/t Au	1.2	
MBDD087	207.00	208.00	1.00	0.77			
MBDD087	210.00	211.00	1.00	0.50	<b>6 m @ 1.16 g/t Au</b>	<b>6.9</b>	
MBDD087	211.00	212.00	1.00	0.07			
MBDD087	212.00	213.00	1.00	0.16			
MBDD087	213.00	214.00	1.00	<b>5.00</b>			
MBDD087	214.00	215.00	1.00	0.49			
MBDD087	215.00	216.00	1.00	0.73			
MBDD088	1.94	3.00	1.06	0.26	<b>8.06 m @ 1.55 g/t Au</b>	<b>12.5</b>	
MBDD088	3.00	4.00	1.00	0.53			
MBDD088	4.00	4.71	0.71	0.06			
MBDD088	4.71	6.00	1.29	<b>6.16</b>			
MBDD088	6.00	7.00	1.00	<b>2.13</b>			
MBDD088	7.00	8.00	1.00	0.25			
MBDD088	8.00	9.00	1.00	0.99			
MBDD088	9.00	10.00	1.00	0.29			
MBDD088	52.19	53.09	0.90	0.36	0.90 m @ 0.36 g/t Au	0.3	

<sup>14</sup> 0.2 g/t Au cut off used with 3m internal dilution and no top cut applied

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
MBDD089A	0.88	1.50	0.62	0.29	2.12 m @ 2.16 g/t Au	4.6	1.50 m @ 2.93 g/t Au
MBDD089A	1.50	3.00	1.50	2.93			
MBDD089A	134.00	135.00	1.00	0.27	1 m @ 0.27 g/t Au	0.3	
MBDD091	127.00	128.00	1.00	0.33	1 m @ 0.33 g/t Au	0.3	
MBDD092	117.00	118.00	1.00	32.12	1 m @ 32.12 g/t Au	32.1	1 m @ 32.12 g/t Au
MBDD093	91.00	92.00	1.00	0.36	1 m @ 0.36 g/t Au	0.4	
MBDD093	102.00	103.00	1.00	0.66	1 m @ 0.66 g/t Au	0.7	
MBDD093	114.00	115.00	1.00	0.54	1 m @ 0.54 g/t Au	0.5	
MBDD093	119.00	120.00	1.00	0.50	1 m @ 0.50 g/t Au	0.5	
MBDD093	136.00	137.00	1.00	0.43	1 m @ 0.43 g/t Au	0.4	
MBDD093	204.00	205.00	1.00	0.21	1 m @ 0.21 g/t Au	0.2	
MBDD094	73.00	74.00	1.00	0.39	4 m @ 0.92 g/t Au	3.7	3 m @ 1.10 g/t Au
MBDD094	74.00	75.00	1.00	1.00			
MBDD094	75.00	76.00	1.00	0.12			
MBDD094	76.00	77.00	1.00	2.17			
MBDD094	90.00	91.00	1.00	0.20	3 m @ 0.29 g/t Au	0.9	
MBDD094	91.00	92.00	1.00	0.38			
MBDD094	92.00	93.00	1.00	0.29			
MBDD094	160.00	161.00	1.00	2.69	1 m @ 2.69 g/t Au	2.7	1 m @ 2.69 g/t Au
MBDD094	173.00	174.00	1.00	0.96	1 m @ 0.96 g/t Au	1.0	
MBDD094	202.00	203.00	1.00	0.39	1 m @ 0.39 g/t Au	0.4	
MBDD095	178.00	179.00	1.00	4.80	3 m @ 2.14 g/t Au	6.4	2 m @ 3.07 g/t Au
MBDD095	179.00	180.00	1.00	1.34			
MBDD095	180.00	181.00	1.00	0.27			
MBDD095	189.00	190.00	1.00	0.27	4 m @ 0.33 g/t Au	1.3	
MBDD095	190.00	191.00	1.00	0.78			
MBDD095	191.00	192.00	1.00	0.05			
MBDD095	192.00	193.00	1.00	0.21			
MBDD096	88.50	89.00	0.50	2.16	0.50 m @ 2.16 g/t Au	1.1	0.50 m @ 2.16 g/t Au
MBDD096	258.00	259.00	1.00	0.24	1 m @ 0.24 g/t Au	0.2	
MBDD097	166.00	167.00	1.00	0.27	1 m @ 0.27 g/t Au	0.3	
MBDD098	7.24	7.87	0.63	0.42	0.63 m @ 0.42 g/t Au	0.3	
MBDD098	56.33	57.26	0.93	38.76	0.93 m @ 38.76 g/t Au	36.0	0.93 m @ 38.76 g/t Au
MBDD098	59.65	60.15	0.50	1.92	0.50 m @ 1.92 g/t Au	1.0	0.50 m @ 1.92 g/t Au
MBDD098	64.28	64.98	0.70	0.62	0.70 m @ 0.62 g/t Au	0.4	
MBDD099A	104.00	105.00	1.00	0.28	2 m @ 0.34 g/t Au	0.7	
MBDD099A	105.00	106.00	1.00	0.40			
MBDD099A	227.00	228.00	1.00	0.32	1 m @ 0.32 g/t Au	0.3	
MBDD099A	279.00	280.00	1.00	0.73	1 m @ 0.73 g/t Au	0.7	
MBDD100	301.00	302.00	1.00	0.24	2 m @ 0.31 g/t Au	0.6	
MBDD100	302.00	303.00	1.00	0.38			
MBDD100	319.00	320.00	1.00	1.12	2 m @ 0.73 g/t Au	1.5	1 m @ 1.12 g/t Au
MBDD100	320.00	321.00	1.00	0.35			
MBDD100	333.00	334.00	1.00	0.56	3 m @ 0.95 g/t Au	2.8	
MBDD100	334.00	335.00	1.00	1.61			
MBDD100	335.00	336.00	1.00	0.67			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
MBDD101A	48.00	49.00	1.00	0.21	1 m @ 0.21 g/t Au	0.2	
MBDD101A	50.00	51.00	1.00	0.21			
MBDD101A	157.00	158.00	1.00	0.82	2 m @ 1.37 g/t Au	2.7	1 m @ 1.92 g/t Au
MBDD101A	158.00	159.00	1.00	1.92			
MBDD102					NSI		
MBDD103	10.00	11.00	1.00	0.30	1 m @ 0.30 g/t Au	0.3	
MBDD103	132.00	133.00	1.00	0.50	1 m @ 0.50 g/t Au	0.5	
MBDD104	248.00	249.10	1.10	0.62	3 m @ 0.92 g/t Au	2.8	1 m @ 1.74 g/t Au
MBDD104	249.10	250.00	0.90	0.37			
MBDD104	250.00	251.00	1.00	1.74			
MBDD104	295.00	296.00	1.00	0.41	1 m @ 0.41 g/t Au	0.4	
MBDD104	306.00	307.00	1.00	0.37	4 m @ 1.07 g/t Au	4.3	1 m @ 3.03 g/t Au
MBDD104	307.00	308.00	1.00	0.59			
MBDD104	308.00	309.00	1.00	3.03			
MBDD104	309.00	310.00	1.00	0.28			
MBDD105					NSI		
MBDD106	94.00	95.00	1.00	0.29	1 m @ 0.29 g/t Au	0.3	
MBDD107	52.00	53.00	1.00	0.29	4 m @ 0.28 g/t Au	1.1	
MBDD107	53.00	54.00	1.00	0.24			
MBDD107	54.00	55.00	1.00	0.24			
MBDD107	55.00	56.00	1.00	0.33			
MBDD107	396.00	397.00	1.00	0.49	1 m @ 0.49 g/t Au	0.5	
MBDD107	585.00	586.00	1.00	0.20	1 m @ 0.20 g/t Au	0.2	
MBDD108	151.00	152.00	1.00	0.87	7 m @ 0.91 g/t Au	6.4	
MBDD108	152.00	153.00	1.00	0.39			
MBDD108	153.00	154.00	1.00	0.14			
MBDD108	154.00	155.00	1.00	0.47			
MBDD108	155.00	156.00	1.00	0.65			
MBDD108	156.00	157.00	1.00	1.42			
MBDD108	157.00	158.00	1.00	2.45	2 m @ 1.94 g/t Au		
MBDD108	207.90	209.00	1.10	2.65	16.10 m @ 0.80 g/t Au	12.8	1.10 m @ 2.65 g/t Au
MBDD108	209.00	210.00	1.00	0.83			
MBDD108	210.00	211.00	1.00	0.45			
MBDD108	211.00	212.00	1.00	0.55			
MBDD108	212.00	213.00	1.00	0.98			
MBDD108	213.00	214.00	1.00	0.67			
MBDD108	214.00	215.00	1.00	1.03			
MBDD108	215.00	216.00	1.00	0.17			
MBDD108	216.00	217.00	1.00	0.26			
MBDD108	217.00	218.00	1.00	2.58			
MBDD108	218.00	219.00	1.00	0.46			
MBDD108	219.00	220.00	1.00	0.48			
MBDD108	220.00	221.00	1.00	0.30			
MBDD108	221.00	222.00	1.00	0.54			
MBDD108	222.00	223.00	1.00	0.20			
MBDD108	223.00	224.00	1.00	0.42			
							4 m @ 1.01 g/t Au

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au	
MBDD108	225.00	226.00	1.00	0.42	9 m @ 0.47 g/t Au	4.2		
MBDD108	226.00	227.00	1.00	0.18				
MBDD108	227.00	228.00	1.00	0.09				
MBDD108	228.00	229.00	1.00	0.81				
MBDD108	229.00	230.00	1.00	0.43				
MBDD108	230.00	231.00	1.00	0.65				
MBDD108	231.00	232.00	1.00	0.25				
MBDD108	232.00	233.00	1.00	<b>1.12</b>				1 m @ 1.12 g/t Au
MBDD108	233.00	234.00	1.00	0.29				
MBDD109	0.00	0.75	0.75	0.90	0.75 m @ 0.90 g/t Au	0.7		
MBDD109	21.00	21.87	0.87	<b>1.00</b>	0.87 m @ 1.00 g/t Au	0.9	0.87 m @ 1.00 g/t Au	
MBDD109	26.00	27.00	1.00	<b>4.03</b>	1 m @ 4.03 g/t Au	4.0	<b>1 m @ 4.03 g/t Au</b>	
MBDD109	159.00	160.00	1.00	<b>1.05</b>	7 m @ 1.27 g/t Au	8.9	5 m @ 1.67 g/t Au	
MBDD109	160.00	161.00	1.00	0.20				
MBDD109	161.00	162.00	1.00	<b>2.09</b>				
MBDD109	162.00	163.00	1.00	<b>3.50</b>				
MBDD109	163.00	164.00	1.00	<b>1.53</b>				
MBDD109	164.00	165.00	1.00	0.06				
MBDD109	165.00	166.00	1.00	0.46				
MBDD109	174.00	175.00	1.00	<b>1.55</b>	5 m @ 1.10 g/t Au	5.5	1 m @ 1.55 g/t Au	
MBDD109	175.00	176.00	1.00	0.01				
MBDD109	176.00	177.00	1.00	0.01				
MBDD109	177.00	178.00	1.00	0.78				
MBDD109	178.00	179.00	1.00	<b>3.15</b>			1 m @ 3.15 g/t Au	
MBDD110	163.00	164.00	1.00	0.20	1 m @ 0.20 g/t Au	0.2		
MBDD110	167.00	168.00	1.00	0.22	1 m @ 0.22 g/t Au	0.2		
MBDD110	195.00	196.00	1.00	0.92	1 m @ 0.92 g/t Au	0.9		
MBDD110	206.00	207.00	1.00	0.28	1 m @ 0.28 g/t Au	0.3		
MBDD110	252.00	253.00	1.00	0.72	6 m @ 2.13 g/t Au	12.8	3 m @ 3.67 g/t Au	
MBDD110	253.00	254.00	1.00	<b>3.51</b>				
MBDD110	254.00	255.00	1.00	<b>2.37</b>				
MBDD110	255.00	256.00	1.00	<b>5.14</b>				
MBDD110	256.00	257.00	1.00	0.79				
MBDD110	257.00	258.00	1.00	0.24	2 m @ 0.79 g/t Au	1.6		
MBDD110	264.00	265.40	1.40	0.98				
MBDD110	265.40	266.00	0.60	0.35				
MBDD110	270.06	271.00	0.94	<b>1.03</b>	4.94 m @ 0.40 g/t Au	2.0	0.94 m @ 1.03 g/t Au	
MBDD110	271.00	272.00	1.00	0.66				
MBDD110	272.00	273.00	1.00	0.06				
MBDD110	273.00	274.00	1.00	0.04				
MBDD110	274.00	275.00	1.00	0.24				
MBDD110	282.00	283.10	1.10	0.26	1.10 m @ 0.26 g/t Au	0.3		
MBDD111	36.00	37.00	1.00	<b>2.86</b>	5 m @ 1.35 g/t Au	6.8	2 m @ 2.81 g/t Au	
MBDD111	37.00	38.00	1.00	<b>2.76</b>				
MBDD111	38.00	39.00	1.00	0.11				
MBDD111	39.00	40.00	1.00	0.16				

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
MBDD111	40.00	41.00	1.00	0.87			
MBDD111	48.00	49.00	1.00	0.20	<b>5 m @ 2.72 g/t Au</b>	<b>13.6</b>	<b>2 m @ 6.28 g/t Au</b>
MBDD111	49.00	50.00	1.00	0.33			
MBDD111	50.00	51.00	1.00	<b>4.28</b>			
MBDD111	51.00	52.00	1.00	<b>8.27</b>			
MBDD111	52.00	53.00	1.00	0.50			
MBDD111	63.00	64.00	1.00	0.56	1 m @ 0.56 g/t Au	0.6	
MBDD112	5.20	6.00	0.80	0.88	<b>3.80 m @ 0.46 g/t Au</b>	<b>1.7</b>	
MBDD112	6.00	7.00	1.00	0.62			
MBDD112	7.00	8.00	1.00	0.01			
MBDD112	8.00	9.00	1.00	0.40			
MBDD112	38.00	39.00	1.00	<b>73.77</b>	<b>1 m @ 73.77 g/t Au</b>	<b>73.8</b>	<b>1 m @ 73.77 g/t Au</b>
MBDD112	43.00	44.00	1.00	<b>16.54</b>	<b>12 m @ 2.14 g/t Au</b>	<b>25.7</b>	<b>1 m @ 16.54 g/t Au</b>
MBDD112	44.00	45.00	1.00	0.97			
MBDD112	45.00	46.00	1.00	0.04			
MBDD112	46.00	47.00	1.00	0.01			
MBDD112	47.00	48.00	1.00	<b>2.69</b>			
MBDD112	48.00	49.00	1.00	0.35			
MBDD112	49.00	50.00	1.00	0.42			
MBDD112	50.00	51.00	1.00	0.50			
MBDD112	51.00	52.00	1.00	<b>1.52</b>			
MBDD112	52.00	53.00	1.00	<b>2.28</b>			
MBDD112	53.00	54.00	1.00	0.13			
MBDD112	54.00	55.00	1.00	0.26			
MBDD112	56.00	57.00	1.00	0.90	<b>6 m @ 4.46 g/t Au</b>	<b>26.8</b>	
MBDD112	57.00	58.00	1.00	0.13			
MBDD112	58.00	59.00	1.00	<b>21.74</b>			
MBDD112	59.00	60.00	1.00	<b>1.65</b>			
MBDD112	60.00	61.00	1.00	<b>2.07</b>			
MBDD112	61.00	62.00	1.00	0.28			
MBDD112	67.00	68.00	1.00	0.34	<b>6 m @ 0.22 g/t Au</b>	<b>1.3</b>	
MBDD112	68.00	69.00	1.00	0.03			
MBDD112	69.00	70.00	1.00	0.08			
MBDD112	70.00	71.00	1.00	0.22			
MBDD112	71.00	72.00	1.00	0.10			
MBDD112	72.00	73.00	1.00	0.54			
MBDD112	97.00	98.00	1.00	0.36	1 m @ 0.36 g/t Au	0.4	
MBDD112	101.00	102.00	1.00	0.59	<b>7 m @ 0.50 g/t Au</b>	<b>3.5</b>	<b>1 m @ 1.06 g/t Au</b>
MBDD112	102.00	103.00	1.00	<b>1.06</b>			
MBDD112	103.00	104.00	1.00	0.20			
MBDD112	104.00	105.00	1.00	0.07			
MBDD112	105.00	106.00	1.00	<b>1.19</b>			
MBDD112	106.00	107.00	1.00	0.01			
MBDD112	107.00	108.00	1.00	0.40			
MBDD112	112.00	113.00	1.00	0.59	<b>3.50 m @ 1.19 g/t Au</b>	<b>4.2</b>	
MBDD112	113.00	114.00	1.00	0.32			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
MBDD112	114.00	115.50	1.50	<b>2.17</b>			<b>1.50 m @ 2.17 g/t Au</b>
MBDD112	132.00	133.00	1.00	0.50	<b>15 m @ 1.17 g/t Au</b>	<b>17.5</b>	
MBDD112	133.00	134.00	1.00	<b>4.63</b>			<b>1 m @ 4.63 g/t Au</b>
MBDD112	134.00	135.00	1.00	0.46			
MBDD112	135.00	136.00	1.00	0.06			
MBDD112	136.00	137.00	1.00	0.65			
MBDD112	137.00	138.00	1.00	<b>7.98</b>			<b>1 m @ 7.98 g/t Au</b>
MBDD112	138.00	139.00	1.00	0.53			
MBDD112	139.00	140.00	1.00	0.23			
MBDD112	140.00	141.00	1.00	0.44			
MBDD112	141.00	142.00	1.00	0.10			
MBDD112	142.00	143.00	1.00	0.82			
MBDD112	143.00	144.00	1.00	0.64			
MBDD112	144.00	145.00	1.00	0.20			
MBDD112	145.00	146.00	1.00	0.02			
MBDD112	146.00	147.00	1.00	0.23			
MBDD112	157.00	158.00	1.00	0.74	<b>4 m @ 0.46 g/t Au</b>	<b>1.9</b>	
MBDD112	158.00	159.00	1.00	0.70			
MBDD112	159.00	160.00	1.00	0.19			
MBDD112	160.00	161.00	1.00	0.22			
MBDD112	166.00	167.00	1.00	<b>1.06</b>	<b>1 m @ 1.06 g/t Au</b>	<b>1.1</b>	<b>1 m @ 1.06 g/t Au</b>
MBDD112	176.00	177.00	1.00	0.83	<b>4 m @ 0.32 g/t Au</b>	<b>1.3</b>	
MBDD112	177.00	178.00	1.00	0.01			
MBDD112	178.00	179.00	1.00	0.12			
MBDD112	179.00	180.00	1.00	0.32			
MBDD113	107.00	108.00	1.00	0.61	<b>1 m @ 0.61 g/t Au</b>	<b>0.6</b>	
MBDD113	123.00	124.00	1.00	0.21	<b>1 m @ 0.21 g/t Au</b>	<b>0.2</b>	
MBDD113	130.00	131.00	1.00	0.82	<b>1 m @ 0.82 g/t Au</b>	<b>0.8</b>	
MBDD113	333.00	334.00	1.00	0.25	<b>1 m @ 0.25 g/t Au</b>	<b>0.3</b>	
MBDD113	373.00	374.00	1.00	0.86	<b>1.93 m @ 0.54 g/t Au</b>	<b>1.0</b>	
MBDD113	374.00	374.93	0.93	0.20			
MBDD113	383.00	384.00	1.00	0.48	<b>1 m @ 0.48 g/t Au</b>	<b>0.5</b>	
MBDD114	60.00	61.30	1.30	0.94	<b>20 m @ 1.61 g/t Au</b>	<b>32.1</b>	
MBDD114	61.30	62.00	0.70	<b>9.97</b>			
MBDD114	62.00	63.00	1.00	<b>3.12</b>			<b>1.70 m @ 5.94 g/t Au</b>
MBDD114	63.00	64.00	1.00	0.18			
MBDD114	64.00	65.00	1.00	0.05			
MBDD114	65.00	66.00	1.00	<b>1.14</b>			
MBDD114	66.00	67.00	1.00	0.42			
MBDD114	67.00	68.00	1.00	0.86			
MBDD114	68.00	69.00	1.00	<b>1.36</b>			<b>7 m @ 1.59 g/t Au</b>
MBDD114	69.00	70.00	1.00	<b>3.49</b>			
MBDD114	70.00	71.00	1.00	<b>1.05</b>			
MBDD114	71.00	72.00	1.00	<b>2.80</b>			
MBDD114	72.00	73.00	1.00	0.83			
MBDD114	73.00	74.00	1.00	0.97			



Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
MBDD114	74.00	75.00	1.00	0.39			
MBDD114	75.00	76.00	1.00	<b>3.02</b>			
MBDD114	76.00	77.00	1.00	<b>1.57</b>			3 m @ 1.97 g/t Au
MBDD114	77.00	78.00	1.00	<b>1.31</b>			
MBDD114	78.00	79.00	1.00	0.87			
MBDD114	79.00	80.00	1.00	0.47			
MBDD114	82.00	83.00	1.00	0.42			
MBDD114	83.00	84.00	1.00	<b>4.48</b>			
MBDD114	84.00	85.00	1.00	<b>4.15</b>	5 m @ 2.76 g/t Au	13.8	3 m @ 4.24 g/t Au
MBDD114	85.00	86.00	1.00	<b>4.10</b>			
MBDD114	86.00	87.00	1.00	0.67			
MBDD114	91.00	92.00	1.00	0.44			
MBDD114	92.00	93.00	1.00	<b>1.42</b>			
MBDD114	93.00	94.00	1.00	<b>1.58</b>	5 m @ 3.12 g/t Au	15.6	4 m @ 3.79 g/t Au
MBDD114	94.00	95.00	1.00	0.21			
MBDD114	95.00	96.00	1.00	<b>11.93</b>			
MBDD114	98.00	99.00	1.00	<b>1.58</b>			
MBDD114	99.00	100.00	1.00	0.12			
MBDD114	100.00	101.00	1.00	0.08			
MBDD114	101.00	102.00	1.00	<b>19.95</b>	6 m @ 3.81 g/t Au	22.9	4 m @ 5.43 g/t Au
MBDD114	102.00	103.00	1.00	0.79			
MBDD114	103.00	104.00	1.00	0.34			
MBDD114	109.00	110.00	1.00	0.65	1 m @ 0.65 g/t Au	0.7	
MBDD114	115.00	116.00	1.00	0.26	2 m @ 0.54 g/t Au	1.1	
MBDD114	116.00	117.00	1.00	0.81			
MBDD114	129.00	130.00	1.00	0.23	1 m @ 0.23 g/t Au	0.2	
MBDD114	151.00	152.00	1.00	0.75	1 m @ 0.75 g/t Au	0.8	
MBDD114	161.00	162.00	1.00	<b>1.18</b>	1 m @ 1.18 g/t Au	1.2	1 m @ 1.18 g/t Au
MBDD114	167.00	168.00	1.00	0.97			
MBDD114	168.00	169.00	1.00	0.77			
MBDD114	169.00	170.00	1.00	0.31	4 m @ 0.71 g/t Au	2.8	
MBDD114	170.00	171.00	1.00	0.78			
MBDD114	179.00	180.00	1.00	0.22			
MBDD114	180.00	181.00	1.00	<b>4.51</b>	2 m @ 2.37 g/t Au	4.7	1 m @ 4.51 g/t Au
MBDD114	186.00	187.00	1.00	0.77			
MBDD114	187.00	188.00	1.00	0.01			
MBDD114	188.00	189.00	1.00	0.02	4 m @ 0.56 g/t Au	2.2	
MBDD114	189.00	190.00	1.00	<b>1.42</b>			1 m @ 1.42 g/t Au
MBDD115					NSI		
MBDD116	38.00	38.57	0.57	0.39	0.57 m @ 0.39 g/t Au	0.2	
MBDD116	39.78	40.50	0.72	0.35	0.72 m @ 0.35 g/t Au	0.3	
MBDD116	351.00	352.00	1.00	0.26	1 m @ 0.26 g/t Au	0.3	
MBDD116	356.00	357.00	1.00	0.66			
MBDD116	357.00	358.00	1.00	0.93			
MBDD116	358.00	359.00	1.00	<b>1.18</b>	4 m @ 1.26 g/t Au	5.0	
MBDD116	359.00	360.00	1.00	<b>2.26</b>			2 m @ 1.72 g/t Au

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au	
MBDD116	372.00	373.00	1.00	<b>3.30</b>	3 m @ 3.01 g/t Au	9.0	2 m @ 4.17 g/t Au	
MBDD116	373.00	374.00	1.00	<b>5.04</b>				
MBDD116	374.00	375.00	1.00	0.70				
MBDD118	31.00	32.19	1.19	<b>277.54</b>	1.19 m @ 277.54 g/t Au	<b>330.3</b>	1.19 m @ 277.54 g/t Au	
MBDD118	33.46	34.50	1.04	0.21	1.04 m @ 0.21 g/t Au	0.2		
MBDD118	36.00	37.00	1.00	0.31	3.50 m @ 0.63 g/t Au	2.2		
MBDD118	37.00	38.00	1.00	0.82				
MBDD118	38.00	39.50	1.50	0.71				
MBDD118	81.00	82.00	1.00	0.38	5.38 m @ 0.46 g/t Au	2.5		
MBDD118	82.00	83.00	1.00	0.03				
MBDD118	83.00	84.00	1.00	0.18				
MBDD118	84.00	85.00	1.00	<b>1.57</b>				1 m @ 1.57 g/t Au
MBDD118	85.00	86.38	1.38	0.25				
MBDD118	91.00	92.00	1.00	0.82				2 m @ 0.67 g/t Au
MBDD118	92.00	93.00	1.00	0.52				
MBDD118	108.00	109.00	1.00	<b>3.06</b>	3 m @ 1.51 g/t Au	4.5		3 m @ 1.51 g/t Au
MBDD118	109.00	110.40	1.40	0.11				
MBDD118	110.40	111.00	0.60	<b>2.19</b>				
MBDD118	121.00	122.00	1.00	0.77	8 m @ 0.40 g/t Au	3.2		
MBDD118	122.00	123.00	1.00	0.31				
MBDD118	123.00	124.00	1.00	0.80				
MBDD118	124.00	125.00	1.00	0.26				
MBDD118	125.00	126.00	1.00	0.05				
MBDD118	126.00	127.00	1.00	0.01				
MBDD118	127.00	128.00	1.00	0.08				
MBDD118	128.00	129.00	1.00	0.92				

**Table 4: Significant assay results for holes being reported for BD<sup>15</sup>**

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0061	9.00	9.67	0.67	0.22	0.67 m @ 0.22 g/t Au	0.1	
DSDD0061	10.50	11.58	1.08	0.34	1.08 m @ 0.34 g/t Au	0.4	
DSDD0061	91.00	92.00	1.00	0.29	5 m @ 0.39 g/t Au	2.0	
DSDD0061	92.00	93.00	1.00	0.12			
DSDD0061	93.00	94.00	1.00	0.75			
DSDD0061	94.00	95.00	1.00	0.44			
DSDD0061	95.00	96.00	1.00	0.37			
DSDD0061	105.00	106.00	1.00	0.81	6.50 m @ 0.38 g/t Au	2.4	
DSDD0061	106.00	107.00	1.00	0.56			
DSDD0061	107.00	108.00	1.00	0.35			
DSDD0061	108.00	109.00	1.00	0.19			
DSDD0061	109.00	110.43	1.43	0.10			
DSDD0061	110.43	111.50	1.07	0.37	2 m @ 0.83 g/t Au	1.7	
DSDD0061	147.00	148.00	1.00	0.87			
DSDD0061	148.00	149.00	1.00	0.79	3 m @ 0.23 g/t Au	0.7	
DSDD0061	168.00	169.00	1.00	0.31			
DSDD0061	169.00	170.00	1.00	0.14			
DSDD0061	170.00	171.00	1.00	0.24	4 m @ 0.29 g/t Au	1.2	
DSDD0061	191.00	192.00	1.00	0.27			
DSDD0061	192.00	193.37	1.37	0.35			
DSDD0061	193.37	194.00	0.63	0.28			
DSDD0061	194.00	195.00	1.00	0.24	1 m @ 0.22 g/t Au	0.2	
DSDD0061	202.00	203.00	1.00	0.22			
DSDD0061	263.00	264.00	1.00	0.48	7 m @ 0.50 g/t Au	3.5	
DSDD0061	264.00	265.00	1.00	0.33			
DSDD0061	265.00	266.00	1.00	0.51			
DSDD0061	266.00	267.00	1.00	0.04			
DSDD0061	267.00	268.00	1.00	0.69			
DSDD0061	268.00	269.00	1.00	0.04			
DSDD0061	269.00	270.00	1.00	<b>1.41</b>			
DSDD0061	275.00	276.00	1.00	0.21	3 m @ 0.58 g/t Au	1.7	
DSDD0061	276.00	277.00	1.00	0.12			
DSDD0061	277.00	278.00	1.00	<b>1.42</b>			
DSDD0061	282.00	283.00	1.00	0.26	2 m @ 0.24 g/t Au	0.5	
DSDD0061	283.00	284.00	1.00	0.22			
DSDD0061	293.00	294.00	1.00	0.33	1 m @ 0.33 g/t Au	0.3	

<sup>15</sup> 0.2 g/t Au cut off used with 3m internal dilution and no top cut applied

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0088B	7.29	8.06	0.77	<b>1.53</b>	0.77 m @ 1.53 g/t Au	1.2	0.77 m @ 1.53 g/t Au
DSDD0088B	29.63	30.32	0.69	<b>1.00</b>	0.69 m @ 1.00 g/t Au	0.7	0.69 m @ 1.00 g/t Au
DSDD0088B	32.72	33.38	0.66	0.30	0.66 m @ 0.30 g/t Au	0.2	
DSDD0088B	57.00	58.00	1.00	0.43	6.06 m @ 1.01 g/t Au	6.1	<b>3.72 m @ 1.43 g/t Au</b>
DSDD0088B	58.00	59.00	1.00	<b>2.22</b>			
DSDD0088B	59.00	60.00	1.00	<b>1.11</b>			
DSDD0088B	60.00	61.00	1.00	0.91			
DSDD0088B	61.00	61.72	0.72	<b>1.48</b>			
DSDD0088B	61.72	63.06	1.34	0.30			
DSDD0088B	65.00	65.55	0.55	0.58	6 m @ 0.30 g/t Au	1.8	
DSDD0088B	65.55	67.00	1.45	0.28			
DSDD0088B	67.00	68.00	1.00	0.11			
DSDD0088B	68.00	69.00	1.00	0.17			
DSDD0088B	69.00	70.00	1.00	0.23			
DSDD0088B	70.00	71.00	1.00	0.57			
DSDD0088B	72.00	73.00	1.00	0.21	9 m @ 0.86 g/t Au	7.8	<b>5 m @ 1.48 g/t Au</b>
DSDD0088B	73.00	74.00	1.00	0.01			
DSDD0088B	74.00	75.00	1.00	0.05			
DSDD0088B	75.00	76.00	1.00	0.12			
DSDD0088B	76.00	77.00	1.00	<b>1.87</b>			
DSDD0088B	77.00	78.00	1.00	<b>3.64</b>			
DSDD0088B	78.00	79.00	1.00	0.29			
DSDD0088B	79.00	80.00	1.00	0.53			
DSDD0088B	80.00	81.00	1.00	<b>1.06</b>	8.50 m @ 0.54 g/t Au	4.6	<b>1 m @ 1.01 g/t Au</b>
DSDD0088B	83.00	84.00	1.00	<b>1.01</b>			
DSDD0088B	84.00	85.00	1.00	0.45			
DSDD0088B	85.00	86.00	1.00	0.83			
DSDD0088B	86.00	87.00	1.00	0.20			
DSDD0088B	87.00	88.00	1.00	<b>1.01</b>			
DSDD0088B	88.00	89.00	1.00	0.39			
DSDD0088B	89.00	90.44	1.44	0.14			
DSDD0088B	90.44	91.50	1.06	0.45	1 m @ 0.49 g/t Au	0.5	
DSDD0088B	96.50	97.50	1.00	0.49			
DSDD0088B	104.71	106.00	1.29	0.38	3.29 m @ 0.22 g/t Au	0.7	
DSDD0088B	106.00	107.00	1.00	0.01			
DSDD0088B	107.00	108.00	1.00	0.24			
DSDD0088B	112.00	113.00	1.00	0.21	1 m @ 0.21 g/t Au	0.2	
DSDD0088B	119.00	120.00	1.00	0.80	1 m @ 0.80 g/t Au	0.8	
DSDD0088B	127.00	128.00	1.00	0.38	9 m @ 0.75 g/t Au	6.7	
DSDD0088B	128.00	129.00	1.00	0.17			
DSDD0088B	129.00	130.00	1.00	0.24			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0088B	130.00	131.00	1.00	0.43			4 m @ 1.13 g/t Au
DSDD0088B	131.00	132.00	1.00	<b>1.21</b>			
DSDD0088B	132.00	133.00	1.00	0.30			
DSDD0088B	133.00	134.00	1.00	0.20			
DSDD0088B	134.00	135.00	1.00	<b>2.82</b>			
DSDD0088B	135.00	136.00	1.00	0.96	3 m @ 0.38 g/t Au	1.1	
DSDD0088B	184.00	185.00	1.00	0.72			
DSDD0088B	185.00	186.00	1.00	0.02			
DSDD0088B	186.00	187.00	1.00	0.41	4 m @ 0.73 g/t Au	2.9	1 m @ 1.25 g/t Au
DSDD0088B	192.00	193.00	1.00	<b>1.25</b>			
DSDD0088B	193.00	194.00	1.00	0.05			
DSDD0088B	194.00	195.00	1.00	0.05			
DSDD0088B	195.00	196.00	1.00	<b>1.56</b>	4 m @ 0.45 g/t Au	1.8	1 m @ 1.56 g/t Au
DSDD0088B	199.00	200.00	1.00	0.60			
DSDD0088B	200.00	201.00	1.00	0.08			
DSDD0088B	201.00	202.00	1.00	0.01			
DSDD0088B	202.00	203.00	1.00	<b>1.11</b>	17 m @ 0.49 g/t Au	8.3	1 m @ 1.11 g/t Au
DSDD0088B	205.00	206.00	1.00	0.40			
DSDD0088B	206.00	207.00	1.00	0.35			
DSDD0088B	207.00	208.00	1.00	0.13			
DSDD0088B	208.00	209.00	1.00	0.22			
DSDD0088B	209.00	210.00	1.00	0.47			
DSDD0088B	210.00	211.00	1.00	0.23			
DSDD0088B	211.00	212.00	1.00	0.28			
DSDD0088B	212.00	213.00	1.00	0.18			
DSDD0088B	213.00	214.00	1.00	0.19			
DSDD0088B	214.00	215.00	1.00	<b>1.75</b>			
DSDD0088B	215.00	216.00	1.00	<b>1.12</b>			
DSDD0088B	216.00	216.85	0.85	0.42			
DSDD0088B	216.85	218.00	1.15	0.40			
DSDD0088B	218.00	219.00	1.00	0.21			
DSDD0088B	219.00	220.00	1.00	0.37			
DSDD0088B	220.00	221.00	1.00	<b>1.10</b>			
DSDD0088B	221.00	222.00	1.00	0.48			
DSDD0088B	227.00	228.00	1.00	0.57	5.79 m @ 0.32 g/t Au	1.9	
DSDD0088B	228.00	229.00	1.00	0.52			
DSDD0088B	229.00	230.00	1.00	0.24			
DSDD0088B	230.00	231.50	1.50	0.08			
DSDD0088B	231.50	232.79	1.29	0.33			
DSDD0088B	242.00	243.00	1.00	0.31	7 m @ 0.71 g/t Au	5.0	
DSDD0088B	243.00	244.00	1.00	0.25			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0088B	244.00	245.00	1.00	0.72			
DSDD0088B	245.00	246.00	1.00	<b>2.81</b>			1 m @ 2.81 g/t Au
DSDD0088B	246.00	247.00	1.00	0.23			
DSDD0088B	247.00	248.00	1.00	0.33			
DSDD0088B	248.00	249.00	1.00	0.33			
DSDD0088B	250.00	251.00	1.00	0.26			
DSDD0088B	251.00	252.30	1.30	<b>3.64</b>			1.30 m @ 3.64 g/t Au
DSDD0088B	252.30	253.00	0.70	0.04			
DSDD0088B	253.00	254.00	1.00	0.49			
DSDD0088B	254.00	255.00	1.00	0.37			
DSDD0088B	255.00	256.00	1.00	0.82			
DSDD0088B	256.00	257.00	1.00	<b>1.00</b>			
DSDD0088B	257.00	258.00	1.00	0.26			
DSDD0088B	258.00	259.00	1.00	0.89	<b>17 m @ 0.84 g/t Au</b>	<b>14.3</b>	<b>6 m @ 1.02 g/t Au</b>
DSDD0088B	259.00	260.00	1.00	<b>1.39</b>			
DSDD0088B	260.00	261.00	1.00	<b>1.43</b>			
DSDD0088B	261.00	262.00	1.00	<b>1.18</b>			
DSDD0088B	262.00	262.70	0.70	0.50			
DSDD0088B	262.70	264.00	1.30	0.02			
DSDD0088B	264.00	265.00	1.00	0.09			
DSDD0088B	265.00	266.08	1.08	0.69			
DSDD0088B	266.08	267.00	0.92	0.23			
DSDD0088B	274.50	276.00	1.50	0.46			
DSDD0088B	276.00	277.00	1.00	0.06			
DSDD0088B	277.00	278.00	1.00	0.24			
DSDD0088B	278.00	279.00	1.00	0.19	<b>6.50 m @ 0.26 g/t Au</b>	<b>1.7</b>	
DSDD0088B	279.00	280.00	1.00	0.27			
DSDD0088B	280.00	281.00	1.00	0.23			
DSDD0088B	295.00	296.00	1.00	<b>2.16</b>			<b>1 m @ 2.16 g/t Au</b>
DSDD0088B	296.00	297.00	1.00	0.22			
DSDD0088B	297.00	298.00	1.00	0.08			
DSDD0088B	298.00	299.00	1.00	0.06	<b>5.75 m @ 0.49 g/t Au</b>	<b>2.8</b>	
DSDD0088B	299.00	300.00	1.00	0.10			
DSDD0088B	300.00	300.75	0.75	0.24			
DSDD0092	134.50	135.50	1.00	0.39	<b>1 m @ 0.39 g/t Au</b>	<b>0.4</b>	
DSDD0092	141.50	142.20	0.70	0.53			
DSDD0092	142.20	143.00	0.80	0.20	<b>1.50 m @ 0.35 g/t Au</b>	<b>0.5</b>	
DSDD0092	172.00	172.90	0.90	0.91			
DSDD0092	172.90	174.00	1.10	0.18	<b>3 m @ 0.54 g/t Au</b>	<b>1.6</b>	
DSDD0092	174.00	175.00	1.00	0.61			
DSDD0094	137.00	137.55	0.55	0.21	<b>0.55 m @ 0.21 g/t Au</b>	<b>0.1</b>	

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0095	96.00	97.00	1.00	0.27	1 m @ 0.27 g/t Au	0.3	
DSDD0095	100.00	101.08	1.08	0.28	1.08 m @ 0.28 g/t Au	0.3	
DSDD0095	102.40	103.00	0.60	0.80	8.60 m @ 0.35 g/t Au	3.0	
DSDD0095	103.00	104.00	1.00	0.16			
DSDD0095	104.00	105.00	1.00	0.17			
DSDD0095	105.00	106.00	1.00	0.30			
DSDD0095	106.00	107.00	1.00	0.60			
DSDD0095	107.00	108.00	1.00	0.16			
DSDD0095	108.00	109.00	1.00	0.36			
DSDD0095	109.00	110.00	1.00	0.55			
DSDD0095	110.00	111.00	1.00	0.23			
DSDD0095	112.00	113.00	1.00	0.36			
DSDD0095	113.00	114.00	1.00	0.11			
DSDD0095	114.00	115.00	1.00	0.12			
DSDD0095	115.00	116.00	1.00	0.31			
DSDD0095	116.00	117.00	1.00	0.20			
DSDD0095	117.00	118.00	1.00	0.37			
DSDD0095	118.00	119.00	1.00	0.38			
DSDD0095	119.00	120.00	1.00	0.78			
DSDD0095	120.00	121.00	1.00	0.26			
DSDD0095	121.00	122.00	1.00	0.25	13 m @ 0.34 g/t Au	4.5	
DSDD0095	122.00	123.00	1.00	0.39			
DSDD0095	133.00	134.00	1.00	0.54			
DSDD0095	134.00	135.00	1.00	0.08			
DSDD0095	135.00	136.00	1.00	0.50			
DSDD0095	136.00	137.00	1.00	0.27			
DSDD0095	137.00	138.00	1.00	0.31			
DSDD0095	138.00	139.00	1.00	0.42			
DSDD0095	139.00	140.00	1.00	0.32			
DSDD0095	140.00	141.00	1.00	0.58			
DSDD0095	141.00	142.00	1.00	0.14			
DSDD0095	142.00	143.00	1.00	0.34			
DSDD0095	143.00	144.00	1.00	0.44			
DSDD0095	144.00	145.00	1.00	0.22			
DSDD0095	145.00	146.00	1.00	0.30			
DSDD0095	152.00	153.00	1.00	0.53			
DSDD0095	153.00	154.00	1.00	0.19			
DSDD0095	154.00	155.00	1.00	0.20			
DSDD0095	155.00	156.00	1.00	0.24			
DSDD0095	156.00	157.00	1.00	0.18			
DSDD0095	157.00	157.96	0.96	0.15			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0095	157.96	159.00	1.04	0.64	5.63 m @ 0.27 g/t Au	1.5	
DSDD0095	205.00	206.00	1.00	0.28			
DSDD0095	206.00	207.00	1.00	0.82			
DSDD0095	207.00	208.00	1.00	0.07			
DSDD0095	208.00	209.00	1.00	0.03			
DSDD0095	209.00	210.00	1.00	0.12			
DSDD0095	210.00	210.63	0.63	0.32			
DSDD0095	212.10	213.00	0.90	0.68			
DSDD0095	213.00	214.00	1.00	<b>2.04</b>	3.90 m @ 0.90 g/t Au	3.5	<b>1 m @ 2.04 g/t Au</b>
DSDD0095	214.00	215.00	1.00	0.66			
DSDD0095	215.00	216.00	1.00	0.20			
DSDD0095	233.00	234.00	1.00	0.22	7 m @ 0.34 g/t Au	2.4	
DSDD0095	234.00	235.00	1.00	0.01			
DSDD0095	235.00	236.00	1.00	0.01			
DSDD0095	236.00	237.00	1.00	0.71			
DSDD0095	237.00	238.00	1.00	0.55			
DSDD0095	238.00	239.00	1.00	0.48			
DSDD0095	239.00	240.00	1.00	0.42			
DSDD0097					NSI		
DSDD0098	35.50	36.50	1.00	0.60	1 m @ 0.60 g/t Au	0.6	
DSDD0098	48.00	49.00	1.00	0.77	3 m @ 0.46 g/t Au	1.4	
DSDD0098	49.00	50.00	1.00	0.36			
DSDD0098	50.00	51.00	1.00	0.24			
DSDD0098	76.00	77.00	1.00	0.34	7 m @ 0.22 g/t Au	1.5	
DSDD0098	77.00	78.00	1.00	0.22			
DSDD0098	78.00	79.00	1.00	0.07			
DSDD0098	79.00	80.00	1.00	0.06			
DSDD0098	80.00	81.48	1.48	0.30			
DSDD0098	81.48	82.00	0.52	0.36			
DSDD0098	82.00	83.00	1.00	0.22			
DSDD0098	92.00	93.00	1.00	0.38	1 m @ 0.38 g/t Au	0.4	
DSDD0098	95.00	96.00	1.00	0.32	12 m @ 0.32 g/t Au	3.9	
DSDD0098	96.00	97.00	1.00	0.21			
DSDD0098	97.00	98.00	1.00	0.13			
DSDD0098	98.00	99.00	1.00	0.37			
DSDD0098	99.00	100.00	1.00	0.39			
DSDD0098	100.00	101.00	1.00	0.09			
DSDD0098	101.00	102.32	1.32	0.26			
DSDD0098	102.32	103.00	0.68	0.13			
DSDD0098	103.00	104.00	1.00	0.24			
DSDD0098	104.00	105.00	1.00	0.67			



Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0098	105.00	106.00	1.00	0.72			
DSDD0098	106.00	107.00	1.00	0.30			
DSDD0098	111.00	112.00	1.00	0.21	1 m @ 0.21 g/t Au	0.2	
DSDD0098	115.00	116.00	1.00	0.22	7 m @ 0.26 g/t Au	1.8	
DSDD0098	116.00	117.50	1.50	0.14			
DSDD0098	117.50	119.00	1.50	0.37			
DSDD0098	119.00	120.00	1.00	0.51			
DSDD0098	120.00	121.00	1.00	0.12			
DSDD0098	121.00	122.00	1.00	0.21	2.30 m @ 0.26 g/t Au	0.6	
DSDD0098	123.00	124.00	1.00	0.24			
DSDD0098	124.00	125.30	1.30	0.28	10.55 m @ 0.66 g/t Au	6.9	
DSDD0098	148.45	149.50	1.05	0.26			
DSDD0098	149.50	151.00	1.50	0.33			
DSDD0098	151.00	152.00	1.00	0.34			
DSDD0098	152.00	152.80	0.80	0.66			
DSDD0098	152.80	154.00	1.20	0.39			
DSDD0098	154.00	155.00	1.00	<b>3.16</b>			
DSDD0098	155.00	156.00	1.00	<b>1.08</b>			
DSDD0098	156.00	157.00	1.00	0.21			
DSDD0098	157.00	158.00	1.00	0.11			
DSDD0098	158.00	159.00	1.00	0.26			
DSDD0098	181.00	182.00	1.00	<b>1.35</b>	1 m @ 1.35 g/t Au	1.4	<b>1 m @ 1.35 g/t Au</b>
DSDD0098	216.00	217.00	1.00	0.71	8 m @ 1.21 g/t Au	9.6	
DSDD0098	217.00	218.00	1.00	0.32			
DSDD0098	218.00	219.00	1.00	0.34			
DSDD0098	219.00	220.00	1.00	0.67			
DSDD0098	220.00	221.00	1.00	0.68			
DSDD0098	221.00	222.00	1.00	0.01			
DSDD0098	222.00	223.00	1.00	<b>6.40</b>			
DSDD0098	223.00	224.00	1.00	0.52			
DSDD0098	227.00	228.00	1.00	<b>1.21</b>	1 m @ 1.21 g/t Au	1.2	<b>1 m @ 1.21 g/t Au</b>
DSDD0098	235.00	236.00	1.00	0.33	7 m @ 0.21 g/t Au	1.5	
DSDD0098	236.00	237.00	1.00	0.11			
DSDD0098	237.00	238.00	1.00	0.01			
DSDD0098	238.00	239.00	1.00	0.01			
DSDD0098	239.00	240.00	1.00	0.50			
DSDD0098	240.00	241.00	1.00	0.30			
DSDD0098	241.00	242.00	1.00	0.24			
DSDD0098	243.00	244.00	1.00	0.54	1 m @ 0.54 g/t Au	0.5	
DSDD0098	250.00	251.00	1.00	<b>1.16</b>	10 m @ 0.54 g/t Au	5.4	<b>1 m @ 1.16 g/t Au</b>
DSDD0098	251.00	252.00	1.00	0.35			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0098	252.00	253.00	1.00	0.19			
DSDD0098	253.00	254.00	1.00	0.28			
DSDD0098	254.00	255.00	1.00	0.39			
DSDD0098	255.00	256.00	1.00	0.59			
DSDD0098	256.00	257.00	1.00	<b>1.58</b>			<b>1 m @ 1.58 g/t Au</b>
DSDD0098	257.00	258.00	1.00	0.20			
DSDD0098	258.00	259.00	1.00	0.14			
DSDD0098	259.00	260.00	1.00	0.52			
DSDD0098	265.00	266.00	1.00	0.30	1 m @ 0.30 g/t Au	0.3	
DSDD0098	270.00	271.00	1.00	0.50			
DSDD0098	271.00	272.00	1.00	0.51	3 m @ 0.69 g/t Au	2.1	
DSDD0098	272.00	273.00	1.00	<b>1.07</b>			<b>1 m @ 1.07 g/t Au</b>
DSDD0098	280.00	281.00	1.00	0.28			
DSDD0098	281.00	282.00	1.00	0.04			
DSDD0098	282.00	282.73	0.73	0.05			
DSDD0098	282.73	284.00	1.27	0.33	7 m @ 0.41 g/t Au	2.8	
DSDD0098	284.00	285.00	1.00	0.89			
DSDD0098	285.00	286.00	1.00	0.82			
DSDD0098	286.00	287.00	1.00	0.36			
DSDD0098	288.00	289.00	1.00	0.27			
DSDD0098	289.00	290.00	1.00	0.14			
DSDD0098	290.00	291.00	1.00	0.65			
DSDD0098	291.00	292.20	1.20	0.08	8 m @ 0.38 g/t Au	3.1	
DSDD0098	292.20	293.00	0.80	0.06			
DSDD0098	293.00	294.00	1.00	0.45			
DSDD0098	294.00	295.00	1.00	0.89			
DSDD0098	295.00	296.00	1.00	0.52			
DSDD0098	297.00	298.00	1.00	0.30			
DSDD0098	298.00	299.00	1.00	0.07	3 m @ 0.24 g/t Au	0.7	
DSDD0098	299.00	300.00	1.00	0.34			
DSDD0098	303.00	304.00	1.00	0.21			
DSDD0098	304.00	305.00	1.00	0.04			
DSDD0098	305.00	306.00	1.00	0.50	5 m @ 0.33 g/t Au	1.6	
DSDD0098	306.00	307.00	1.00	0.05			
DSDD0098	307.00	308.00	1.00	0.83			
DSDD0098	310.00	311.00	1.00	0.28			
DSDD0098	311.00	312.00	1.00	0.41			
DSDD0098	312.00	313.00	1.00	0.32			
DSDD0098	313.00	314.00	1.00	<b>1.45</b>	7 m @ 0.48 g/t Au	3.3	<b>1 m @ 1.45 g/t Au</b>
DSDD0098	314.00	315.00	1.00	0.22			
DSDD0098	315.00	316.00	1.00	0.40			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0098	316.00	317.00	1.00	0.25			
DSDD0098	326.00	327.00	1.00	0.20	1 m @ 0.20 g/t Au	0.2	
DSDD0098	330.00	331.00	1.00	0.36			
DSDD0098	331.00	332.00	1.00	0.43			
DSDD0098	332.00	333.00	1.00	0.17			
DSDD0098	333.00	334.00	1.00	0.30			
DSDD0098	334.00	335.00	1.00	0.46			
DSDD0098	335.00	336.00	1.00	0.34			
DSDD0098	336.00	337.00	1.00	0.25			
DSDD0098	337.00	338.00	1.00	0.44			
DSDD0098	338.00	339.00	1.00	0.45			
DSDD0098	339.00	340.00	1.00	0.28			
DSDD0098	340.00	341.00	1.00	0.31	21 m @ 0.45 g/t Au	9.5	
DSDD0098	341.00	342.00	1.00	0.60			
DSDD0098	342.00	343.14	1.14	0.46			
DSDD0098	343.14	344.00	0.86	0.11			
DSDD0098	344.00	345.00	1.00	0.25			
DSDD0098	345.00	346.00	1.00	0.55			
DSDD0098	346.00	347.00	1.00	0.69			
DSDD0098	347.00	348.00	1.00	0.85			
DSDD0098	348.00	349.00	1.00	0.48			
DSDD0098	349.00	350.00	1.00	0.09			
DSDD0098	350.00	351.00	1.00	<b>1.57</b>			1 m @ 1.57 g/t Au
DSDD0098	355.00	356.00	1.00	<b>4.16</b>			1 m @ 4.16 g/t Au
DSDD0098	356.00	357.00	1.00	0.15			
DSDD0098	357.00	358.00	1.00	0.06			
DSDD0098	358.00	359.00	1.00	0.45			
DSDD0098	359.00	360.00	1.00	<b>3.73</b>	10 m @ 1.10 g/t Au	11.0	1 m @ 3.73 g/t Au
DSDD0098	360.00	361.00	1.00	0.45			
DSDD0098	361.00	362.00	1.00	0.16			
DSDD0098	362.00	363.00	1.00	0.32			
DSDD0098	363.00	364.00	1.00	<b>1.10</b>			1 m @ 1.10 g/t Au
DSDD0098	364.00	365.00	1.00	0.39			
DSDD0098	366.00	367.00	1.00	0.39	2 m @ 0.30 g/t Au	0.6	
DSDD0098	367.00	368.00	1.00	0.21			
DSDD0098	371.00	372.00	1.00	0.21	1 m @ 0.21 g/t Au	0.2	
DSDD0099A	3.95	4.70	0.75	0.38	0.75 m @ 0.38 g/t Au	0.3	
DSDD0099A	39.00	40.00	1.00	0.23	1 m @ 0.23 g/t Au	0.2	
DSDD0099A	67.00	68.00	1.00	0.58	1 m @ 0.58 g/t Au	0.6	
DSDD0099A	99.00	100.00	1.00	0.25	1 m @ 0.25 g/t Au	0.3	
DSDD0100	1.50	3.00	1.50	0.21	1.50 m @ 0.21 g/t Au	0.3	

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0100	6.55	7.62	1.07	0.29	1.07 m @ 0.29 g/t Au	0.3	
DSDD0100	17.85	19.07	1.22	0.63	1.22 m @ 0.63 g/t Au	0.8	
DSDD0100	20.15	21.00	0.85	0.27	19.85 m @ 0.42 g/t Au	8.3	
DSDD0100	21.00	22.00	1.00	0.18			
DSDD0100	22.00	23.29	1.29	0.28			
DSDD0100	23.29	24.00	0.71	<b>1.44</b>			
DSDD0100	24.00	25.00	1.00	<b>1.06</b>			
DSDD0100	25.00	26.00	1.00	0.24			
DSDD0100	26.00	27.00	1.00	0.19			
DSDD0100	27.00	28.00	1.00	0.38			
DSDD0100	28.00	29.00	1.00	0.33			
DSDD0100	29.00	30.00	1.00	0.30			
DSDD0100	30.00	31.00	1.00	0.27			
DSDD0100	31.00	32.00	1.00	0.22			
DSDD0100	32.00	33.00	1.00	0.60			
DSDD0100	33.00	34.00	1.00	0.50			
DSDD0100	34.00	35.00	1.00	0.24			
DSDD0100	35.00	36.00	1.00	0.24			
DSDD0100	36.00	37.00	1.00	0.20			
DSDD0100	37.00	38.00	1.00	<b>1.14</b>			
DSDD0100	38.00	39.00	1.00	0.33			
DSDD0100	39.00	40.00	1.00	0.30			
DSDD0100	50.15	51.00	0.85	0.24	0.85 m @ 0.24 g/t Au	0.2	
DSDD0100	101.00	102.00	1.00	0.57	7 m @ 0.39 g/t Au	2.7	
DSDD0100	102.00	103.00	1.00	0.41			
DSDD0100	103.00	104.00	1.00	0.10			
DSDD0100	104.00	105.00	1.00	0.27			
DSDD0100	105.00	106.00	1.00	<b>1.09</b>			
DSDD0100	106.00	107.00	1.00	0.09			
DSDD0100	107.00	108.00	1.00	0.20			
DSDD0100	111.00	112.00	1.00	0.23	1 m @ 0.23 g/t Au	0.2	
DSDD0100	131.00	132.19	1.19	0.39	11 m @ 0.63 g/t Au	6.9	
DSDD0100	132.19	133.00	0.81	0.13			
DSDD0100	133.00	134.00	1.00	0.23			
DSDD0100	134.00	135.00	1.00	0.25			
DSDD0100	135.00	136.00	1.00	0.30			
DSDD0100	136.00	137.00	1.00	0.53			
DSDD0100	137.00	138.00	1.00	<b>1.36</b>			
DSDD0100	138.00	139.00	1.00	<b>1.35</b>			
DSDD0100	139.00	140.00	1.00	0.19			
DSDD0100	140.00	141.00	1.00	<b>1.62</b>			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0100	141.00	142.00	1.00	0.50			
DSDD0100	179.00	180.00	1.00	<b>5.01</b>	1 m @ 5.01 g/t Au	5.0	<b>1 m @ 5.01 g/t Au</b>
DSDD0100	200.00	201.00	1.00	0.20	1 m @ 0.20 g/t Au	0.2	
DSDD0100	203.00	204.00	1.00	0.28	1 m @ 0.28 g/t Au	0.3	
DSDD0100	206.00	207.00	1.00	0.20	1 m @ 0.20 g/t Au	0.2	
DSDD0100	209.00	210.00	1.00	0.24	1 m @ 0.24 g/t Au	0.2	
DSDD0100	231.43	232.00	0.57	0.24	5.57 m @ 0.32 g/t Au	1.8	
DSDD0100	232.00	233.00	1.00	0.38			
DSDD0100	233.00	234.00	1.00	0.01			
DSDD0100	234.00	235.00	1.00	0.39			
DSDD0100	235.00	236.00	1.00	0.20			
DSDD0100	236.00	237.00	1.00	0.67			
DSDD0100	244.00	245.00	1.00	0.25	1 m @ 0.25 g/t Au	0.3	
DSDD0100	252.00	253.00	1.00	0.29	1 m @ 0.29 g/t Au	0.3	
DSDD0100	254.00	255.00	1.00	0.24	1 m @ 0.24 g/t Au	0.2	
DSDD0100	256.00	257.00	1.00	0.27	1 m @ 0.27 g/t Au	0.3	
DSDD0101	151.00	152.00	1.00	0.40	<b>3 m @ 3.44 g/t Au</b>	<b>10.3</b>	
DSDD0101	152.00	153.00	1.00	0.30			
DSDD0101	153.00	154.00	1.00	<b>9.61</b>			<b>1 m @ 9.61 g/t Au</b>
DSDD0101	212.14	213.00	0.86	<b>1.28</b>	0.86 m @ 1.28 g/t Au	1.1	0.86 m @ 1.28 g/t Au
DSDD0101	233.00	234.00	1.00	<b>1.25</b>	3 m @ 0.93 g/t Au	2.8	<b>2 m @ 1.30 g/t Au</b>
DSDD0101	234.00	235.00	1.00	<b>1.35</b>			
DSDD0101	235.00	236.00	1.00	0.20			
DSDD0101	260.00	261.00	1.00	0.39	1 m @ 0.39 g/t Au	0.4	
DSDD0101	266.00	267.00	1.00	0.25	1 m @ 0.25 g/t Au	0.3	
DSDD0101	273.00	274.00	1.00	0.32	1 m @ 0.32 g/t Au	0.3	
DSDD0101	275.00	276.00	1.00	0.62	7 m @ 0.28 g/t Au	2.0	
DSDD0101	276.00	277.00	1.00	0.22			
DSDD0101	277.00	278.00	1.00	0.18			
DSDD0101	278.00	279.00	1.00	0.07			
DSDD0101	279.00	280.00	1.00	0.08			
DSDD0101	280.00	281.00	1.00	0.33			
DSDD0101	281.00	282.00	1.00	0.48			
DSDD0102					NSI		
DSDD0103	114.00	115.50	1.50	0.36	1.50 m @ 0.36 g/t Au	0.5	
DSDD0104	67.98	69.00	1.02	0.53	4.02 m @ 0.33 g/t Au	1.3	
DSDD0104	69.00	70.00	1.00	0.24			
DSDD0104	70.00	71.00	1.00	0.10			
DSDD0104	71.00	72.00	1.00	0.43	5 m @ 0.37 g/t Au	1.8	
DSDD0104	74.00	75.00	1.00	0.80			
DSDD0104	75.00	76.05	1.05	0.08			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0104	76.05	77.00	0.95	0.17			
DSDD0104	77.00	78.00	1.00	0.55			
DSDD0104	78.00	79.00	1.00	0.25			
DSDD0104	89.00	90.00	1.00	0.45	2 m @ 0.33 g/t Au	0.7	
DSDD0104	90.00	91.00	1.00	0.21			
DSDD0104	97.00	97.61	0.61	0.20	4 m @ 0.25 g/t Au	1.0	
DSDD0104	97.61	99.00	1.39	0.33			
DSDD0104	99.00	100.00	1.00	0.02			
DSDD0104	100.00	101.00	1.00	0.39			
DSDD0104	108.00	109.00	1.00	0.25	2 m @ 0.28 g/t Au	0.6	
DSDD0104	109.00	110.00	1.00	0.30			
DSDD0104	114.00	115.00	1.00	<b>1.23</b>	1 m @ 1.23 g/t Au	1.2	<b>1 m @ 1.23 g/t Au</b>
DSDD0104	125.00	126.00	1.00	0.23	1 m @ 0.23 g/t Au	0.2	
DSDD0104	136.00	137.00	1.00	0.30	13 m @ 0.26 g/t Au	3.4	
DSDD0104	137.00	138.00	1.00	0.37			
DSDD0104	138.00	139.00	1.00	0.35			
DSDD0104	139.00	140.07	1.07	0.26			
DSDD0104	140.07	141.00	0.93	0.34			
DSDD0104	141.00	142.00	1.00	0.21			
DSDD0104	142.00	143.00	1.00	0.15			
DSDD0104	143.00	143.52	0.52	0.10			
DSDD0104	143.52	145.00	1.48	0.22			
DSDD0104	145.00	146.00	1.00	0.05			
DSDD0104	146.00	147.00	1.00	0.25			
DSDD0104	147.00	148.00	1.00	0.41			
DSDD0104	148.00	149.00	1.00	0.33			
DSDD0104	155.00	156.33	1.33	0.22	9 m @ 0.23 g/t Au	2.1	
DSDD0104	156.33	157.00	0.67	0.33			
DSDD0104	157.00	158.00	1.00	0.16			
DSDD0104	158.00	159.00	1.00	0.35			
DSDD0104	159.00	160.00	1.00	0.20			
DSDD0104	160.00	161.00	1.00	0.31			
DSDD0104	161.00	162.00	1.00	0.12			
DSDD0104	162.00	163.00	1.00	0.21			
DSDD0104	163.00	164.00	1.00	0.23			
DSDD0104	170.00	171.00	1.00	0.23	5 m @ 0.29 g/t Au	1.5	
DSDD0104	171.00	172.00	1.00	0.23			
DSDD0104	172.00	173.00	1.00	0.16			
DSDD0104	173.00	174.00	1.00	0.48			
DSDD0104	174.00	175.00	1.00	0.37			
DSDD0104	179.00	180.00	1.00	0.24	1 m @ 0.24 g/t Au	0.2	

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0104	183.00	184.00	1.00	0.23	10 m @ 0.23 g/t Au	2.3	
DSDD0104	184.00	185.00	1.00	0.09			
DSDD0104	185.00	186.00	1.00	0.43			
DSDD0104	186.00	187.00	1.00	0.22			
DSDD0104	187.00	188.00	1.00	0.20			
DSDD0104	188.00	189.00	1.00	0.14			
DSDD0104	189.00	190.00	1.00	0.15			
DSDD0104	190.00	191.00	1.00	0.25			
DSDD0104	191.00	192.00	1.00	0.22			
DSDD0104	192.00	193.00	1.00	0.33			
DSDD0104	199.00	200.00	1.00	0.46	5 m @ 0.28 g/t Au	1.4	
DSDD0104	200.00	201.00	1.00	0.46			
DSDD0104	201.00	202.00	1.00	0.13			
DSDD0104	202.00	203.00	1.00	0.04			
DSDD0104	203.00	204.00	1.00	0.30			
DSDD0104	213.00	214.00	1.00	0.22	2 m @ 0.66 g/t Au	1.3	1 m @ 1.10 g/t Au
DSDD0104	214.00	215.00	1.00	<b>1.10</b>			
DSDD0104	219.00	220.00	1.00	0.37	7 m @ 0.34 g/t Au	2.3	
DSDD0104	220.00	221.00	1.00	0.82			
DSDD0104	221.00	222.00	1.00	0.16			
DSDD0104	222.00	223.00	1.00	0.44			
DSDD0104	223.00	224.00	1.00	0.19			
DSDD0104	224.00	225.00	1.00	0.16			
DSDD0104	225.00	226.00	1.00	0.21			
DSDD0104	231.00	232.00	1.00	0.71	6 m @ 0.33 g/t Au	2.0	
DSDD0104	232.00	233.00	1.00	0.09			
DSDD0104	233.00	234.00	1.00	0.02			
DSDD0104	234.00	235.00	1.00	0.03			
DSDD0104	235.00	236.00	1.00	0.81			
DSDD0104	236.00	237.00	1.00	0.33			
DSDD0104	240.00	241.00	1.00	0.35	8 m @ 0.23 g/t Au	1.8	
DSDD0104	241.00	242.00	1.00	0.21			
DSDD0104	242.00	243.00	1.00	0.18			
DSDD0104	243.00	244.00	1.00	0.30			
DSDD0104	244.00	245.00	1.00	0.15			
DSDD0104	245.00	246.00	1.00	0.05			
DSDD0104	246.00	247.00	1.00	0.35			
DSDD0104	247.00	248.00	1.00	0.25			
DSDD0104	255.00	256.00	1.00	0.22	1 m @ 0.22 g/t Au	0.2	
DSDD0104	257.00	258.00	1.00	0.37	7 m @ 0.26 g/t Au	1.8	
DSDD0104	258.00	259.00	1.00	0.11			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0104	259.00	260.00	1.00	0.14			
DSDD0104	260.00	261.00	1.00	0.25			
DSDD0104	261.00	262.00	1.00	0.29			
DSDD0104	262.00	263.00	1.00	0.16			
DSDD0104	263.00	264.00	1.00	0.50			
DSDD0104	268.00	269.00	1.00	0.22	1 m @ 0.22 g/t Au	0.2	
DSDD0104	284.00	285.00	1.00	0.22			
DSDD0104	285.00	286.00	1.00	0.10			
DSDD0104	286.00	287.00	1.00	0.07			
DSDD0104	287.00	288.00	1.00	0.39			
DSDD0104	288.00	289.00	1.00	0.39	8 m @ 0.34 g/t Au	2.8	
DSDD0104	289.00	290.00	1.00	0.17			
DSDD0104	290.00	291.00	1.00	<b>1.11</b>			1 m @ 1.11 g/t Au
DSDD0104	291.00	292.00	1.00	0.31			
DSDD0104	293.00	294.00	1.00	0.58			
DSDD0104	294.00	294.57	0.57	0.24			
DSDD0104	294.57	295.34	0.77	0.26	3.59 m @ 0.41 g/t Au	1.5	
DSDD0104	295.34	296.59	1.25	0.43			
DSDD0104	299.70	301.00	1.30	0.57			
DSDD0104	301.00	302.00	1.00	0.03			
DSDD0104	302.00	303.00	1.00	0.03			
DSDD0104	303.00	304.00	1.00	0.06	6.30 m @ 0.58 g/t Au	3.6	
DSDD0104	304.00	305.00	1.00	<b>2.10</b>			1 m @ 2.10 g/t Au
DSDD0104	305.00	306.00	1.00	0.67			
DSDD0105	88.00	89.00	1.00	0.21	1 m @ 0.21 g/t Au	0.2	
DSDD0105	90.88	92.00	1.12	0.23	1.12 m @ 0.23 g/t Au	0.3	
DSDD0105	134.00	135.00	1.00	0.26			
DSDD0105	135.00	136.00	1.00	0.07			
DSDD0105	136.00	137.00	1.00	0.36	3 m @ 0.23 g/t Au	0.7	
DSDD0105	192.00	193.00	1.00	0.22	1 m @ 0.22 g/t Au	0.2	
DSDD0105	198.00	199.00	1.00	0.29			
DSDD0105	199.00	200.00	1.00	0.06			
DSDD0105	200.00	201.00	1.00	0.13			
DSDD0105	201.00	202.00	1.00	0.40	4 m @ 0.22 g/t Au	0.9	
DSDD0105	203.00	204.00	1.00	0.21	1 m @ 0.21 g/t Au	0.2	
DSDD0105	211.00	212.00	1.00	0.20			
DSDD0105	212.00	213.00	1.00	0.18			
DSDD0105	213.00	214.00	1.00	0.11			
DSDD0105	214.00	215.00	1.00	0.39	4 m @ 0.22 g/t Au	0.9	
DSDD0105	216.00	217.00	1.00	0.82			
DSDD0105	217.00	218.00	1.00	<b>1.08</b>	7 m @ 0.36 g/t Au	2.5	1 m @ 1.08 g/t Au



Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0105	218.00	219.00	1.00	0.02			
DSDD0105	219.00	220.00	1.00	0.03			
DSDD0105	220.00	221.00	1.00	0.01			
DSDD0105	221.00	222.00	1.00	0.25			
DSDD0105	222.00	223.00	1.00	0.30			
DSDD0105	225.00	226.00	1.00	0.22	1 m @ 0.22 g/t Au	0.2	
DSDD0106					NSI		
DSDD0107	10.00	10.91	0.91	<b>2.97</b>	0.91 m @ 2.97 g/t Au	2.7	0.91 m @ 2.97 g/t Au
DSDD0107	42.00	43.00	1.00	0.31			
DSDD0107	43.00	44.00	1.00	0.36	2 m @ 0.34 g/t Au	0.7	
DSDD0108					NSI		
DSDD0109	278.00	279.00	1.00	0.31	1 m @ 0.31 g/t Au	0.3	
DSDD0110	86.00	87.00	1.00	0.62	1 m @ 0.62 g/t Au	0.6	
DSDD0110	103.00	104.00	1.00	0.24	1 m @ 0.24 g/t Au	0.2	
DSDD0110	109.00	110.00	1.00	<b>12.26</b>	<b>1 m @ 12.26 g/t Au</b>	<b>12.3</b>	<b>1 m @ 12.26 g/t Au</b>
DSDD0110	115.50	117.00	1.50	0.78	1.50 m @ 0.78 g/t Au	1.2	
DSDD0110	121.22	122.00	0.78	0.83			
DSDD0110	122.00	123.00	1.00	0.48			
DSDD0110	123.00	124.00	1.00	0.28			
DSDD0110	124.00	125.00	1.00	0.01			
DSDD0110	125.00	126.00	1.00	<b>11.57</b>			
DSDD0110	126.00	127.00	1.00	0.42			
DSDD0110	127.00	128.00	1.00	<b>1.01</b>			
DSDD0110	128.00	129.00	1.00	<b>1.35</b>			
DSDD0110	129.00	130.00	1.00	<b>2.55</b>	<b>15.78 m @ 1.70 g/t Au</b>	<b>26.8</b>	<b>6 m @ 2.99 g/t Au</b>
DSDD0110	130.00	131.00	1.00	<b>1.05</b>			
DSDD0110	131.00	132.00	1.00	0.74			
DSDD0110	132.00	133.00	1.00	0.17			
DSDD0110	133.00	134.00	1.00	0.59			
DSDD0110	134.00	135.00	1.00	<b>2.75</b>			
DSDD0110	135.00	136.00	1.00	0.02			<b>3 m @ 1.98 g/t Au</b>
DSDD0110	136.00	137.00	1.00	<b>3.17</b>			
DSDD0110	168.00	169.00	1.00	<b>3.47</b>			<b>1 m @ 3.47 g/t Au</b>
DSDD0110	169.00	170.00	1.00	0.81			
DSDD0110	170.00	171.00	1.00	0.01			
DSDD0110	171.00	172.00	1.00	0.01	7 m @ 1.01 g/t Au	7.1	
DSDD0110	172.00	173.00	1.00	0.01			
DSDD0110	173.00	174.00	1.00	0.59			
DSDD0110	174.00	175.00	1.00	<b>2.20</b>			<b>1 m @ 2.20 g/t Au</b>
DSDD0110	185.00	186.00	1.00	<b>2.17</b>			<b>1 m @ 2.17 g/t Au</b>
DSDD0110	186.00	187.00	1.00	0.85	2 m @ 1.51 g/t Au	3.0	

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0110	188.00	189.00	1.00	0.35	6 m @ 0.24 g/t Au	1.5	
DSDD0110	189.00	190.00	1.00	0.01			
DSDD0110	190.00	191.00	1.00	0.01			
DSDD0110	191.00	192.00	1.00	0.01			
DSDD0110	192.00	193.34	1.34	0.67			
DSDD0110	193.34	194.00	0.66	0.31			
DSDD0110	239.00	240.00	1.00	0.31	1 m @ 0.31 g/t Au	0.3	
DSDD0110	242.00	243.00	1.00	0.39	4 m @ 0.24 g/t Au	1.0	
DSDD0110	243.00	244.00	1.00	0.01			
DSDD0110	244.00	245.00	1.00	0.01			
DSDD0110	245.00	246.00	1.00	0.56			
DSDD0110	250.00	251.00	1.00	0.62	1 m @ 0.62 g/t Au	0.6	
DSDD0110	255.00	256.00	1.00	0.20	1 m @ 0.20 g/t Au	0.2	
DSDD0110	279.00	280.00	1.00	<b>5.14</b>	4 m @ 1.52 g/t Au	6.1	<b>1 m @ 5.14 g/t Au</b>
DSDD0110	280.00	281.00	1.00	0.18			
DSDD0110	281.00	282.00	1.00	0.13			
DSDD0110	282.00	283.00	1.00	0.63			
DSDD0110	288.00	289.00	1.00	<b>3.56</b>	1 m @ 3.56 g/t Au	3.6	<b>1 m @ 3.56 g/t Au</b>
DSDD0110	294.00	295.00	1.00	0.70	3 m @ 0.60 g/t Au	1.8	
DSDD0110	295.00	296.00	1.00	0.63			
DSDD0110	296.00	297.00	1.00	0.47			
DSDD0110	303.00	304.00	1.00	0.21	1 m @ 0.21 g/t Au	0.2	
DSDD0111	45.00	46.00	1.00	0.94	1 m @ 0.94 g/t Au	0.9	
DSDD0111	66.00	67.50	1.50	0.22	11 m @ 0.24 g/t Au	2.6	
DSDD0111	67.50	69.00	1.50	0.27			
DSDD0111	69.00	70.00	1.00	0.28			
DSDD0111	70.00	71.00	1.00	0.07			
DSDD0111	71.00	72.00	1.00	0.46			
DSDD0111	72.00	73.00	1.00	0.27			
DSDD0111	73.00	74.00	1.00	0.28			
DSDD0111	74.00	75.00	1.00	0.13			
DSDD0111	75.00	76.00	1.00	0.14			
DSDD0111	76.00	77.00	1.00	0.25			
DSDD0111	83.00	84.00	1.00	0.60			1 m @ 0.60 g/t Au
DSDD0111	93.00	94.00	1.00	0.36	1 m @ 0.36 g/t Au	0.4	
DSDD0112					NSI		
DSDD0113	4.48	5.03	0.55	0.24	0.55 m @ 0.24 g/t Au	0.1	
DSDD0113	106.00	107.00	1.00	0.23	1 m @ 0.23 g/t Au	0.2	
DSDD0113	236.00	237.00	1.00	0.24	6 m @ 0.65 g/t Au	3.9	
DSDD0113	237.00	238.00	1.00	0.23			
DSDD0113	238.00	239.00	1.00	0.15			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0113	239.00	240.00	1.00	0.06			
DSDD0113	240.00	241.00	1.00	0.29			
DSDD0113	241.00	242.00	1.00	<b>2.95</b>			<b>1 m @ 2.95 g/t Au</b>
DSDD0113	244.00	245.00	1.00	0.26			
DSDD0113	245.00	246.00	1.00	0.36	3 m @ 0.46 g/t Au	1.4	
DSDD0113	246.00	247.00	1.00	0.77			
DSDD0113	248.00	249.00	1.00	<b>1.45</b>			<b>1 m @ 1.45 g/t Au</b>
DSDD0113	249.00	250.00	1.00	0.07			
DSDD0113	250.00	251.00	1.00	0.07			
DSDD0113	251.00	252.00	1.00	0.28	7 m @ 0.50 g/t Au	3.5	
DSDD0113	252.00	253.00	1.00	0.67			
DSDD0113	253.00	254.00	1.00	0.10			
DSDD0113	254.00	255.00	1.00	0.84			
DSDD0113	264.00	265.00	1.00	0.74	1 m @ 0.74 g/t Au	0.7	
DSDD0114	228.00	229.00	1.00	<b>1.06</b>			<b>1 m @ 1.06 g/t Au</b>
DSDD0114	229.00	230.00	1.00	0.83	2 m @ 0.94 g/t Au	1.9	
DSDD0115	2.00	3.45	1.45	0.29	1.45 m @ 0.29 g/t Au	0.4	
DSDD0115	136.00	137.00	1.00	0.35	1 m @ 0.35 g/t Au	0.4	
DSDD0115	139.00	140.00	1.00	0.67			
DSDD0115	140.00	141.00	1.00	0.07			
DSDD0115	141.00	142.00	1.00	0.19	5 m @ 0.25 g/t Au	1.3	
DSDD0115	142.00	143.00	1.00	0.12			
DSDD0115	143.00	144.00	1.00	0.20			
DSDD0115	146.00	147.00	1.00	0.22			
DSDD0115	147.00	148.00	1.00	0.24			
DSDD0115	148.00	149.00	1.00	0.29	5 m @ 0.32 g/t Au	1.6	
DSDD0115	149.00	150.00	1.00	0.53			
DSDD0115	150.00	151.00	1.00	0.32			
DSDD0115	155.00	156.00	1.00	0.47			
DSDD0115	156.00	157.00	1.00	0.03	4 m @ 0.27 g/t Au	1.1	
DSDD0115	157.00	158.00	1.00	0.01			
DSDD0115	158.00	159.00	1.00	0.59			
DSDD0115	174.00	175.00	1.00	0.47			
DSDD0115	175.00	176.21	1.21	0.39	3 m @ 0.39 g/t Au	1.2	
DSDD0115	176.21	177.00	0.79	0.28			
DSDD0115	183.00	184.00	1.00	0.31			
DSDD0115	184.00	185.00	1.00	0.15			
DSDD0115	185.00	186.00	1.00	0.28			
DSDD0115	186.00	187.00	1.00	0.05	6 m @ 0.35 g/t Au	2.1	
DSDD0115	187.00	188.00	1.00	0.62			
DSDD0115	188.00	189.00	1.00	0.67			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0115	197.00	197.87	0.87	0.29	0.87 m @ 0.29 g/t Au	0.3	
DSDD0115	218.00	219.00	1.00	0.44	3 m @ 0.43 g/t Au	1.3	
DSDD0115	219.00	220.00	1.00	0.50			
DSDD0115	220.00	221.00	1.00	0.36			
DSDD0116					NSI		
DSDD0117	10.00	11.49	1.49	0.20	1.49 m @ 0.20 g/t Au	0.3	
DSDD0117	186.00	187.00	1.00	0.40	2 m @ 0.34 g/t Au	0.7	
DSDD0117	187.00	188.00	1.00	0.28			
DSDD0117	191.00	192.00	1.00	<b>4.36</b>	5 m @ 1.15 g/t Au	5.8	<b>1 m @ 4.36 g/t Au</b>
DSDD0117	192.00	193.00	1.00	0.06			
DSDD0117	193.00	194.00	1.00	0.04			
DSDD0117	194.00	195.00	1.00	0.07			
DSDD0117	195.00	196.00	1.00	<b>1.22</b>			<b>1 m @ 1.22 g/t Au</b>
DSDD0117	222.00	223.00	1.00	0.27	1 m @ 0.27 g/t Au	0.3	
DSDD0117	232.59	234.00	1.41	<b>6.87</b>	<b>3.41 m @ 3.01 g/t Au</b>	<b>10.3</b>	<b>1.41 m @ 6.87 g/t Au</b>
DSDD0117	234.00	235.00	1.00	0.21			
DSDD0117	235.00	236.00	1.00	0.36			
DSDD0117	237.00	238.00	1.00	0.55	7 m @ 0.35 g/t Au	2.4	
DSDD0117	238.00	239.00	1.00	0.41			
DSDD0117	239.00	240.00	1.00	0.75			
DSDD0117	240.00	241.00	1.00	0.17			
DSDD0117	241.00	242.00	1.00	0.03			
DSDD0117	242.00	243.00	1.00	0.13			
DSDD0117	243.00	244.00	1.00	0.38			
DSDD0117	245.00	246.00	1.00	<b>1.17</b>	1 m @ 1.17 g/t Au	1.2	<b>1 m @ 1.17 g/t Au</b>
DSDD0117	250.00	251.00	1.00	0.45	1 m @ 0.45 g/t Au	0.5	
DSDD0118					NSI		
DSDD0119	75.00	76.00	1.00	0.39	1 m @ 0.39 g/t Au	0.4	
DSDD0119	117.00	118.00	1.00	0.37	1 m @ 0.37 g/t Au	0.4	
DSDD0119	125.00	126.00	1.00	0.37			
DSDD0119	286.00	287.00	1.00	0.27	1 m @ 0.27 g/t Au	0.3	
DSDD0120	60.47	61.00	0.53	0.92	0.53 m @ 0.92 g/t Au	0.5	
DSDD0120	71.00	72.00	1.00	0.29	1 m @ 0.29 g/t Au	0.3	
DSDD0120	74.00	75.00	1.00	0.42	7 m @ 0.23 g/t Au	1.6	
DSDD0120	75.00	76.00	1.00	0.28			
DSDD0120	76.00	77.00	1.00	0.20			
DSDD0120	77.00	78.00	1.00	0.16			
DSDD0120	78.00	79.00	1.00	0.12			
DSDD0120	79.00	80.00	1.00	0.18			
DSDD0120	80.00	81.00	1.00	0.23			
DSDD0120	85.00	86.00	1.00	<b>1.25</b>	8 m @ 0.57 g/t Au	4.6	<b>1 m @ 1.25 g/t Au</b>

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0120	86.00	87.00	1.00	0.39			
DSDD0120	87.00	88.00	1.00	0.18			
DSDD0120	88.00	89.00	1.00	0.55			
DSDD0120	89.00	90.00	1.00	<b>1.32</b>			<b>1 m @ 1.32 g/t Au</b>
DSDD0120	90.00	91.00	1.00	0.05			
DSDD0120	91.00	92.00	1.00	0.08			
DSDD0120	92.00	93.00	1.00	0.75			
DSDD0120	94.00	95.00	1.00	0.32			
DSDD0120	95.00	96.00	1.00	0.32			
DSDD0120	96.00	97.00	1.00	0.04			
DSDD0120	97.00	98.00	1.00	0.05	7.50 m @ 0.20 g/t Au	1.5	
DSDD0120	98.00	99.00	1.00	0.28			
DSDD0120	99.00	100.00	1.00	0.19			
DSDD0120	100.00	101.50	1.50	0.22			
DSDD0120	102.66	104.00	1.34	<b>1.08</b>			<b>1.34 m @ 1.08 g/t Au</b>
DSDD0120	104.00	105.00	1.00	0.08			
DSDD0120	105.00	106.00	1.00	0.04	5.34 m @ 0.48 g/t Au	2.6	
DSDD0120	106.00	107.00	1.00	0.13			
DSDD0120	107.00	108.00	1.00	0.87			
DSDD0120	109.00	110.00	1.00	<b>1.66</b>			
DSDD0120	110.00	111.00	1.00	<b>7.02</b>	4 m @ 2.32 g/t Au	9.3	<b>2 m @ 4.34 g/t Au</b>
DSDD0120	111.00	111.79	0.79	0.09			
DSDD0120	111.79	113.00	1.21	0.43			
DSDD0120	131.00	132.00	1.00	0.59	1 m @ 0.59 g/t Au	0.6	
DSDD0120	148.00	149.00	1.00	0.58	1 m @ 0.58 g/t Au	0.6	
DSDD0120	180.00	181.00	1.00	0.24	1 m @ 0.24 g/t Au	0.2	
DSDD0120	197.00	198.00	1.00	0.43	1 m @ 0.43 g/t Au	0.4	
DSDD0120	205.00	206.00	1.00	0.33			
DSDD0120	206.00	207.00	1.00	0.46			
DSDD0120	207.00	208.00	1.00	0.48	4 m @ 0.71 g/t Au	2.8	
DSDD0120	208.00	209.00	1.00	<b>1.56</b>			<b>1 m @ 1.56 g/t Au</b>
DSDD0120	216.00	217.00	1.00	0.36			
DSDD0120	217.00	218.00	1.00	0.58			
DSDD0120	218.00	219.00	1.00	0.14			
DSDD0120	219.00	220.00	1.00	<b>1.24</b>			<b>1 m @ 1.24 g/t Au</b>
DSDD0120	220.00	221.00	1.00	0.01			
DSDD0120	221.00	222.00	1.00	0.13	10 m @ 0.42 g/t Au	4.2	
DSDD0120	222.00	223.00	1.00	0.40			
DSDD0120	223.00	224.00	1.00	0.20			
DSDD0120	224.00	225.00	1.00	0.57			
DSDD0120	225.00	226.00	1.00	0.56			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0120	238.28	239.00	0.72	1.29	0.72 m @ 1.29 g/t Au	0.9	0.72 m @ 1.29 g/t Au
DSDD0120	268.50	270.00	1.50	0.67	1.50 m @ 0.67 g/t Au	1.0	
DSDD0120	298.00	299.00	1.00	1.55	1 m @ 1.55 g/t Au	1.6	1 m @ 1.55 g/t Au
DSDD0121	40.00	41.00	1.00	0.26	1 m @ 0.26 g/t Au	0.3	
DSDD0121	72.00	73.00	1.00	0.38	1 m @ 0.38 g/t Au	0.4	
DSDD0121	288.00	289.00	1.00	0.25	1 m @ 0.25 g/t Au	0.3	
DSDD0121	394.00	395.00	1.00	3.17			1 m @ 3.17 g/t Au
DSDD0121	395.00	396.00	1.00	0.91			
DSDD0121	396.00	397.00	1.00	0.27			
DSDD0121	397.00	398.00	1.00	0.11			
DSDD0121	398.00	399.00	1.00	0.36			
DSDD0121	399.00	400.00	1.00	0.91	10 m @ 0.71 g/t Au	7.1	
DSDD0121	400.00	401.00	1.00	0.79			
DSDD0121	401.00	402.00	1.00	0.10			
DSDD0121	402.00	403.00	1.00	0.18			
DSDD0121	403.00	404.00	1.00	0.27			
DSDD0121	412.00	413.00	1.00	0.20	1 m @ 0.20 g/t Au	0.2	
DSDD0121	419.00	420.00	1.00	0.31			
DSDD0121	420.00	421.00	1.00	0.14			
DSDD0121	421.00	422.00	1.00	0.13			
DSDD0121	422.00	423.00	1.00	0.25	6 m @ 0.23 g/t Au	1.4	
DSDD0121	423.00	424.00	1.00	0.18			
DSDD0121	424.00	425.00	1.00	0.38			
DSDD0121	437.00	438.00	1.00	0.32			
DSDD0121	438.00	439.00	1.00	0.44			
DSDD0121	439.00	440.00	1.00	0.26			
DSDD0121	440.00	441.00	1.00	0.26			
DSDD0121	441.00	442.00	1.00	0.23			
DSDD0121	442.00	443.00	1.00	0.52			
DSDD0121	443.00	444.00	1.00	0.13			
DSDD0121	444.00	445.00	1.00	0.32	14 m @ 0.27 g/t Au	3.8	
DSDD0121	445.00	446.00	1.00	0.13			
DSDD0121	446.00	447.00	1.00	0.22			
DSDD0121	447.00	448.00	1.00	0.20			
DSDD0121	448.00	449.00	1.00	0.30			
DSDD0121	449.00	450.00	1.00	0.28			
DSDD0121	450.00	451.00	1.00	0.21			
DSDD0121	455.00	456.00	1.00	0.41	1 m @ 0.41 g/t Au	0.4	
DSDD0121	457.00	458.00	1.00	0.20			
DSDD0121	458.00	459.00	1.00	0.22	11 m @ 0.35 g/t Au	3.8	
DSDD0121	459.00	460.00	1.00	0.23			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0121	460.00	461.00	1.00	0.57			
DSDD0121	461.00	462.00	1.00	0.19			
DSDD0121	462.00	463.00	1.00	0.02			
DSDD0121	463.00	464.00	1.00	0.04			
DSDD0121	464.00	465.00	1.00	0.32			
DSDD0121	465.00	466.00	1.00	0.40			
DSDD0121	466.00	467.00	1.00	<b>1.22</b>			<b>1 m @ 1.22 g/t Au</b>
DSDD0121	467.00	468.00	1.00	0.41			
DSDD0121	469.00	470.00	1.00	0.50			
DSDD0121	470.00	471.00	1.00	0.17	3 m @ 0.57 g/t Au	1.7	
DSDD0121	471.00	472.00	1.00	<b>1.05</b>			
DSDD0121	473.00	474.00	1.00	0.25			
DSDD0121	474.00	475.00	1.00	<b>22.60</b>			<b>4 m @ 6.01 g/t Au</b>
DSDD0121	475.00	476.00	1.00	0.20			
DSDD0121	476.00	477.00	1.00	0.42			
DSDD0121	477.00	478.00	1.00	0.06			
DSDD0121	478.00	479.00	1.00	0.13	10 m @ 2.43 g/t Au	24.3	
DSDD0121	479.00	480.00	1.00	0.02			
DSDD0121	480.00	481.00	1.00	0.21			
DSDD0121	481.00	482.00	1.00	0.24			
DSDD0121	482.00	483.00	1.00	0.20			
DSDD0121	487.00	488.00	1.00	0.22			
DSDD0121	488.00	489.00	1.00	<b>1.20</b>			<b>1 m @ 1.20 g/t Au</b>
DSDD0121	489.00	490.00	1.00	0.54			
DSDD0121	490.00	491.00	1.00	0.32			
DSDD0121	491.00	492.00	1.00	0.63			
DSDD0121	492.00	493.00	1.00	0.68			
DSDD0121	493.00	494.00	1.00	0.24			
DSDD0121	494.00	495.00	1.00	0.86	15 m @ 0.69 g/t Au	10.4	
DSDD0121	495.00	496.00	1.00	<b>1.10</b>			<b>2 m @ 1.23 g/t Au</b>
DSDD0121	496.00	497.00	1.00	<b>1.36</b>			
DSDD0121	497.00	498.00	1.00	0.94			
DSDD0121	498.00	499.00	1.00	0.31			
DSDD0121	499.00	500.00	1.00	0.60			
DSDD0121	500.00	501.00	1.00	0.42			
DSDD0121	501.00	502.00	1.00	0.99			
DSDD0121	503.00	504.00	1.00	0.29			
DSDD0121	504.00	505.00	1.00	0.45			
DSDD0121	505.00	506.00	1.00	<b>1.19</b>	21 m @ 0.45 g/t Au	9.5	<b>1 m @ 1.19 g/t Au</b>
DSDD0121	506.00	507.00	1.00	0.32			
DSDD0121	507.00	508.00	1.00	0.23			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0121	508.00	509.00	1.00	0.78			
DSDD0121	509.00	510.00	1.00	0.20			
DSDD0121	510.00	511.00	1.00	0.92			
DSDD0121	511.00	512.00	1.00	0.03			
DSDD0121	512.00	513.00	1.00	0.13			
DSDD0121	513.00	514.00	1.00	0.73			
DSDD0121	514.00	515.00	1.00	0.78			
DSDD0121	515.00	516.00	1.00	0.27			
DSDD0121	516.00	517.00	1.00	0.32			
DSDD0121	517.00	518.00	1.00	0.65			
DSDD0121	518.00	519.00	1.00	0.20			
DSDD0121	519.00	520.00	1.00	0.52			
DSDD0121	520.00	521.00	1.00	0.12			
DSDD0121	521.00	522.00	1.00	0.21			
DSDD0121	522.00	523.00	1.00	0.83			
DSDD0121	523.00	524.00	1.00	0.29			
DSDD0121	525.00	526.00	1.00	0.51	19 m @ 0.45 g/t Au	8.6	1 m @ 1.47 g/t Au
DSDD0121	526.00	527.00	1.00	<b>1.47</b>			
DSDD0121	527.00	528.00	1.00	0.60			
DSDD0121	528.00	529.00	1.00	0.20			
DSDD0121	529.00	530.00	1.00	0.07			
DSDD0121	530.00	531.00	1.00	0.28			
DSDD0121	531.00	532.00	1.00	0.43			
DSDD0121	532.00	533.00	1.00	0.38			
DSDD0121	533.00	534.00	1.00	0.09			
DSDD0121	534.00	535.00	1.00	0.07			
DSDD0121	535.00	536.00	1.00	0.44			
DSDD0121	536.00	537.00	1.00	0.40			
DSDD0121	537.00	538.00	1.00	0.37			
DSDD0121	538.00	539.00	1.00	0.31			
DSDD0121	539.00	540.00	1.00	0.69			
DSDD0121	540.00	541.00	1.00	0.74			
DSDD0121	541.00	542.00	1.00	0.73			
DSDD0121	542.00	543.00	1.00	0.54			
DSDD0121	543.00	544.00	1.00	0.25			
DSDD0121	545.00	546.09	1.09	0.43	5 m @ 0.34 g/t Au	1.7	
DSDD0121	546.09	547.00	0.91	0.17			
DSDD0121	547.00	548.41	1.41	0.05			
DSDD0121	548.41	549.00	0.59	0.73			
DSDD0121	549.00	550.00	1.00	0.58	NSI		
DSDD0122							



Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0123A	26.68	27.78	1.10	0.64	1.10 m @ 0.64 g/t Au	0.7	
DSDD0123A	49.50	50.40	0.90	0.22	0.90 m @ 0.22 g/t Au	0.2	
DSDD0123A	51.00	52.00	1.00	0.42	2.47 m @ 2.87 g/t Au	7.1	
DSDD0123A	52.00	53.47	1.47	<b>4.54</b>			<b>1.47 m @ 4.54 g/t Au</b>
DSDD0123A	54.00	55.00	1.00	0.22	9.97 m @ 0.51 g/t Au	5.1	
DSDD0123A	55.00	56.00	1.00	0.14			
DSDD0123A	56.00	57.00	1.00	0.40			
DSDD0123A	57.00	58.00	1.00	0.29			
DSDD0123A	58.00	59.00	1.00	<b>1.05</b>			<b>1 m @ 1.05 g/t Au</b>
DSDD0123A	59.00	60.00	1.00	0.39			
DSDD0123A	60.00	61.00	1.00	0.31			
DSDD0123A	61.00	62.00	1.00	0.17			
DSDD0123A	62.00	63.00	1.00	0.76			
DSDD0123A	63.00	63.97	0.97	<b>1.43</b>			0.97 m @ 1.43 g/t Au
DSDD0123A	64.50	65.00	0.50	0.56			7.50 m @ 0.44 g/t Au
DSDD0123A	65.00	66.00	1.00	0.43			
DSDD0123A	66.00	67.00	1.00	0.71			
DSDD0123A	67.00	68.00	1.00	0.16			
DSDD0123A	68.00	69.00	1.00	0.18			
DSDD0123A	69.00	70.00	1.00	<b>1.14</b>	<b>1 m @ 1.14 g/t Au</b>		
DSDD0123A	70.00	71.00	1.00	0.06			
DSDD0123A	71.00	72.00	1.00	0.31			
DSDD0123A	75.22	76.00	0.78	<b>1.72</b>	1.78 m @ 1.46 g/t Au	2.6	<b>1.78 m @ 1.46 g/t Au</b>
DSDD0123A	76.00	77.00	1.00	<b>1.25</b>			
DSDD0123A	82.00	83.00	1.00	0.31	1 m @ 0.31 g/t Au	0.3	
DSDD0123A	96.00	97.00	1.00	0.37	1 m @ 0.37 g/t Au	0.4	
DSDD0123A	106.00	107.00	1.00	0.22	3 m @ 0.73 g/t Au	2.2	
DSDD0123A	107.00	108.00	1.00	0.47			
DSDD0123A	108.00	109.00	1.00	<b>1.50</b>			<b>1 m @ 1.50 g/t Au</b>
DSDD0123A	218.00	219.00	1.00	0.65	2 m @ 0.51 g/t Au	1.0	
DSDD0123A	219.00	220.00	1.00	0.36			
DSDD0123A	226.00	227.00	1.00	0.21	1 m @ 0.21 g/t Au	0.2	
DSDD0123A	232.00	233.00	1.00	0.43	1 m @ 0.43 g/t Au	0.4	
DSDD0123A	263.00	264.00	1.00	0.64	1 m @ 0.64 g/t Au	0.6	
DSDD0123A	283.00	284.00	1.00	0.60	1 m @ 0.60 g/t Au	0.6	
DSDD0123A	313.00	314.00	1.00	0.37	14 m @ 0.68 g/t Au	9.5	
DSDD0123A	314.00	315.00	1.00	0.72			
DSDD0123A	315.00	316.00	1.00	0.28			
DSDD0123A	316.00	317.00	1.00	0.32			
DSDD0123A	317.00	318.00	1.00	0.05			
DSDD0123A	318.00	319.00	1.00	0.87			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0123A	319.00	320.00	1.00	0.99			
DSDD0123A	320.00	321.00	1.00	0.06			
DSDD0123A	321.00	322.00	1.00	0.09			
DSDD0123A	322.00	323.00	1.00	0.73			
DSDD0123A	323.00	324.00	1.00	<b>1.28</b>			
DSDD0123A	324.00	325.00	1.00	0.62			<b>3 m @ 1.54 g/t Au</b>
DSDD0123A	325.00	326.00	1.00	<b>2.72</b>			
DSDD0123A	326.00	327.00	1.00	0.36			
DSDD0123A	328.00	329.00	1.00	<b>1.18</b>			<b>1 m @ 1.18 g/t Au</b>
DSDD0123A	329.00	330.00	1.00	0.86			
DSDD0123A	330.00	331.00	1.00	0.12	<b>5 m @ 0.60 g/t Au</b>	<b>3.0</b>	
DSDD0123A	331.00	332.00	1.00	0.61			
DSDD0123A	332.00	333.00	1.00	0.22			
DSDD0123A	334.00	335.00	1.00	0.74			
DSDD0123A	335.00	336.00	1.00	<b>1.40</b>			<b>1 m @ 1.40 g/t Au</b>
DSDD0123A	336.00	337.00	1.00	0.07			
DSDD0123A	337.00	338.00	1.00	0.12	<b>6 m @ 0.48 g/t Au</b>	<b>2.9</b>	
DSDD0123A	338.00	339.00	1.00	0.13			
DSDD0123A	339.00	340.00	1.00	0.42			
DSDD0123A	341.00	342.00	1.00	0.73			
DSDD0123A	342.00	343.00	1.00	0.60			
DSDD0123A	343.00	344.00	1.00	0.35			
DSDD0123A	344.00	345.00	1.00	0.42			
DSDD0123A	345.00	346.00	1.00	0.33			
DSDD0123A	346.00	347.00	1.00	0.37			
DSDD0123A	347.00	348.00	1.00	<b>4.66</b>			
DSDD0123A	348.00	349.00	1.00	<b>3.00</b>			
DSDD0123A	349.00	350.00	1.00	0.30			<b>6 m @ 2.03 g/t Au</b>
DSDD0123A	350.00	351.00	1.00	<b>1.06</b>			
DSDD0123A	351.00	352.00	1.00	0.96	<b>33 m @ 0.84 g/t Au</b>	<b>27.7</b>	
DSDD0123A	352.00	353.00	1.00	<b>2.22</b>			
DSDD0123A	353.00	354.00	1.00	0.41			
DSDD0123A	354.00	355.00	1.00	0.43			
DSDD0123A	355.00	356.00	1.00	0.08			
DSDD0123A	356.00	357.00	1.00	0.11			
DSDD0123A	357.00	358.00	1.00	<b>1.81</b>			
DSDD0123A	358.00	359.00	1.00	0.62			<b>3 m @ 1.18 g/t Au</b>
DSDD0123A	359.00	360.00	1.00	<b>1.12</b>			
DSDD0123A	360.00	361.00	1.00	0.85			
DSDD0123A	361.00	362.00	1.00	0.68			
DSDD0123A	362.00	363.00	1.00	0.38			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0123A	363.00	364.00	1.00	0.65			
DSDD0123A	364.00	365.00	1.00	0.18			
DSDD0123A	365.00	366.00	1.00	0.28			
DSDD0123A	366.00	367.00	1.00	0.77			
DSDD0123A	367.00	368.00	1.00	0.48			
DSDD0123A	368.00	369.00	1.00	0.73			
DSDD0123A	369.00	370.00	1.00	<b>1.47</b>			
DSDD0123A	370.00	371.00	1.00	0.55			
DSDD0123A	371.00	372.00	1.00	0.20			
DSDD0123A	372.00	372.97	0.97	0.29			
DSDD0123A	372.97	374.00	1.03	0.57			
DSDD0123A	377.00	378.00	1.00	0.80			
DSDD0123A	378.00	379.00	1.00	0.37			
DSDD0123A	379.00	379.53	0.53	0.38			
DSDD0123A	379.53	381.00	1.47	0.42			
DSDD0123A	381.00	382.10	1.10	0.32			
DSDD0123A	382.10	383.00	0.90	0.69			
DSDD0123A	383.00	384.00	1.00	<b>14.79</b>	<b>13.88 m @ 1.45 g/t Au</b>	<b>20.1</b>	<b>1 m @ 14.79 g/t Au</b>
DSDD0123A	384.00	385.00	1.00	0.83			
DSDD0123A	385.00	386.00	1.00	0.29			
DSDD0123A	386.00	387.00	1.00	0.12			
DSDD0123A	387.00	388.00	1.00	0.13			
DSDD0123A	388.00	389.00	1.00	0.26			
DSDD0123A	389.00	390.00	1.00	0.43			
DSDD0123A	390.00	390.88	0.88	0.31			
DSDD0123A	394.00	395.00	1.00	0.49			
DSDD0123A	395.00	396.00	1.00	0.24			
DSDD0123A	396.00	397.00	1.00	<b>1.05</b>			<b>1 m @ 1.05 g/t Au</b>
DSDD0123A	397.00	398.00	1.00	0.54			
DSDD0123A	398.00	399.00	1.00	0.35			
DSDD0123A	399.00	400.00	1.00	0.57			
DSDD0123A	400.00	401.00	1.00	0.15			
DSDD0123A	401.00	402.00	1.00	<b>1.46</b>	<b>22 m @ 0.57 g/t Au</b>	<b>12.6</b>	<b>1 m @ 1.46 g/t Au</b>
DSDD0123A	402.00	403.00	1.00	0.46			
DSDD0123A	403.00	404.00	1.00	0.99			
DSDD0123A	404.00	405.00	1.00	0.41			
DSDD0123A	405.00	406.00	1.00	0.32			
DSDD0123A	406.00	407.00	1.00	0.62			
DSDD0123A	407.00	408.00	1.00	0.78			
DSDD0123A	408.00	409.00	1.00	0.51			
DSDD0123A	409.00	410.00	1.00	0.59			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au	
DSDD0123A	410.00	411.00	1.00	0.73				
DSDD0123A	411.00	412.00	1.00	0.21				
DSDD0123A	412.00	413.00	1.00	0.20				
DSDD0123A	413.00	414.00	1.00	0.23				
DSDD0123A	414.00	415.00	1.00	0.13				
DSDD0123A	415.00	416.00	1.00	<b>1.57</b>			<b>1 m @ 1.57 g/t Au</b>	
DSDD0123A	418.00	419.00	1.00	<b>1.85</b>			<b>1 m @ 1.85 g/t Au</b>	
DSDD0123A	419.00	420.00	1.00	0.12	4 m @ 0.71 g/t Au	2.9		
DSDD0123A	420.00	421.00	1.00	0.17				
DSDD0123A	421.00	422.00	1.00	0.72				
DSDD0123A	424.00	425.00	1.00	0.79				
DSDD0123A	425.00	426.00	1.00	0.13	4.50 m @ 0.41 g/t Au	1.8		
DSDD0123A	426.00	427.00	1.00	0.06				
DSDD0123A	427.00	428.50	1.50	0.58				
DSDD0124	182.00	183.00	1.00	0.23	1 m @ 0.23 g/t Au	0.2		
DSDD0124	195.00	196.00	1.00	0.60	4 m @ 0.24 g/t Au	0.9		
DSDD0124	196.00	197.00	1.00	0.01				
DSDD0124	197.00	198.00	1.00	0.04				
DSDD0124	198.00	199.00	1.00	0.30				
DSDD0124	204.00	205.00	1.00	0.41	7 m @ 0.27 g/t Au	1.9		
DSDD0124	205.00	206.00	1.00	0.01				
DSDD0124	206.00	207.00	1.00	0.14				
DSDD0124	207.00	208.00	1.00	0.08				
DSDD0124	208.00	209.00	1.00	0.47				
DSDD0124	209.00	210.00	1.00	0.28				
DSDD0124	210.00	211.00	1.00	0.51				
DSDD0124	218.00	219.00	1.00	0.23	15 m @ 0.52 g/t Au	7.8		
DSDD0124	219.00	220.00	1.00	0.25				
DSDD0124	220.00	221.00	1.00	0.40				
DSDD0124	221.00	222.00	1.00	0.36				
DSDD0124	222.00	223.00	1.00	<b>1.10</b>		<b>1 m @ 1.10 g/t Au</b>		
DSDD0124	223.00	224.00	1.00	0.82				
DSDD0124	224.00	225.00	1.00	0.61				
DSDD0124	225.00	226.00	1.00	0.46				
DSDD0124	226.00	227.00	1.00	0.98				
DSDD0124	227.00	228.00	1.00	0.44				
DSDD0124	228.00	229.00	1.00	0.44				
DSDD0124	229.00	230.00	1.00	0.13				
DSDD0124	230.00	231.00	1.00	0.82				
DSDD0124	231.00	232.00	1.00	0.33				
DSDD0124	232.00	233.00	1.00	0.45				

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au	
DSDD0124	269.04	270.00	0.96	<b>75.02</b>	<b>0.96 m @ 75.02 g/t Au</b>	<b>72.0</b>	<b>0.96 m @ 75.02 g/t Au</b>	
DSDD0124	310.00	311.00	1.00	0.40	1 m @ 0.40 g/t Au	0.4		
DSDD0124	331.00	332.00	1.00	0.20	1 m @ 0.20 g/t Au	0.2		
DSDD0124	369.00	370.00	1.00	<b>1.16</b>	2.42 m @ 0.66 g/t Au	1.6	<b>1 m @ 1.16 g/t Au</b>	
DSDD0124	370.00	371.42	1.42	0.30				
DSDD0124	387.56	389.00	1.44	0.21	7.44 m @ 0.31 g/t Au	2.3		
DSDD0124	389.00	390.00	1.00	0.01				
DSDD0124	390.00	391.00	1.00	0.01				
DSDD0124	391.00	392.00	1.00	0.22				
DSDD0124	392.00	393.00	1.00	0.59				
DSDD0124	393.00	394.00	1.00	0.60				
DSDD0124	394.00	395.00	1.00	0.55				
DSDD0124	396.00	397.00	1.00	0.97	5 m @ 0.30 g/t Au	1.5		
DSDD0124	397.00	398.00	1.00	0.15				
DSDD0124	398.00	399.00	1.00	0.04				
DSDD0124	399.00	400.00	1.00	0.15				
DSDD0124	400.00	401.00	1.00	0.20				
DSDD0124	408.00	409.00	1.00	0.57	1 m @ 0.57 g/t Au	0.6		
DSDD0124	410.89	412.00	1.11	0.29	12.11 m @ 0.49 g/t Au	5.9		
DSDD0124	412.00	413.00	1.00	<b>1.05</b>				<b>1 m @ 1.05 g/t Au</b>
DSDD0124	413.00	414.00	1.00	0.48				
DSDD0124	414.00	415.00	1.00	0.14				
DSDD0124	415.00	416.00	1.00	0.54				
DSDD0124	416.00	417.00	1.00	0.29				
DSDD0124	417.00	418.00	1.00	0.93				
DSDD0124	418.00	419.00	1.00	0.24				
DSDD0124	419.00	420.00	1.00	0.11				
DSDD0124	420.00	421.00	1.00	0.33				
DSDD0124	421.00	422.00	1.00	0.44				
DSDD0124	422.00	423.00	1.00	<b>1.02</b>				
DSDD0124	427.00	428.00	1.00	0.76	1 m @ 0.76 g/t Au	0.8		
DSDD0124	430.00	431.00	1.00	0.32	10 m @ 0.51 g/t Au	5.1		
DSDD0124	431.00	431.80	0.80	0.10				
DSDD0124	431.80	433.00	1.20	0.06				
DSDD0124	433.00	434.00	1.00	0.19				
DSDD0124	434.00	435.00	1.00	0.64				
DSDD0124	435.00	435.69	0.69	0.23				
DSDD0124	435.69	437.00	1.31	<b>1.95</b>				<b>1.31 m @ 1.95 g/t Au</b>
DSDD0124	437.00	438.00	1.00	0.33				
DSDD0124	438.00	439.00	1.00	0.42				
DSDD0124	439.00	440.00	1.00	0.32				

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0124	444.00	445.00	1.00	<b>3.80</b>	17 m @ 0.75 g/t Au	12.7	1 m @ 3.80 g/t Au
DSDD0124	445.00	446.00	1.00	0.77			
DSDD0124	446.00	447.00	1.00	0.21			
DSDD0124	447.00	448.00	1.00	0.50			
DSDD0124	448.00	449.00	1.00	0.23			
DSDD0124	449.00	450.00	1.00	<b>2.64</b>			1 m @ 2.64 g/t Au
DSDD0124	450.00	451.00	1.00	0.56			
DSDD0124	451.00	452.00	1.00	0.60			
DSDD0124	452.00	453.00	1.00	0.77			
DSDD0124	453.00	454.00	1.00	0.60			
DSDD0124	454.00	455.00	1.00	0.31			
DSDD0124	455.00	456.00	1.00	0.11			
DSDD0124	456.00	457.00	1.00	0.47			
DSDD0124	457.00	458.00	1.00	0.48			
DSDD0124	458.00	459.00	1.00	0.14			
DSDD0124	459.00	460.00	1.00	0.30			
DSDD0124	460.00	461.00	1.00	0.21			18 m @ 0.41 g/t Au
DSDD0124	462.00	463.00	1.00	0.54			
DSDD0124	463.00	464.00	1.00	0.61			
DSDD0124	464.00	465.00	1.00	0.27			
DSDD0124	465.00	466.00	1.00	0.40			
DSDD0124	466.00	467.00	1.00	0.49			
DSDD0124	467.00	468.00	1.00	0.73			
DSDD0124	468.00	469.00	1.00	0.70			
DSDD0124	469.00	470.00	1.00	0.49			
DSDD0124	470.00	471.00	1.00	0.65			
DSDD0124	471.00	472.00	1.00	0.48			
DSDD0124	472.00	473.00	1.00	0.15			
DSDD0124	473.00	474.00	1.00	0.29			
DSDD0124	474.00	475.00	1.00	0.49			
DSDD0124	475.00	476.00	1.00	0.51			
DSDD0124	476.00	477.00	1.00	0.25			
DSDD0124	477.00	478.00	1.00	0.06			
DSDD0124	478.00	479.00	1.00	0.06			
DSDD0124	479.00	480.00	1.00	0.29	5 m @ 6.55 g/t Au	32.7	
DSDD0124	481.00	482.00	1.00	<b>31.94</b>			1 m @ 31.94 g/t Au
DSDD0124	482.00	483.00	1.00	0.06			
DSDD0124	483.00	484.00	1.00	0.19			
DSDD0124	484.00	485.00	1.00	0.15			
DSDD0124	485.00	486.00	1.00	0.40	21.39 m @ 1.07 g/t Au	23.0	
DSDD0124	489.00	490.00	1.00	0.46			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0124	490.00	491.00	1.00	0.56			
DSDD0124	491.00	492.00	1.00	0.20			
DSDD0124	492.00	493.00	1.00	<b>1.01</b>			<b>1 m @ 1.01 g/t Au</b>
DSDD0124	493.00	494.00	1.00	0.40			
DSDD0124	494.00	495.00	1.00	0.12			
DSDD0124	495.00	496.00	1.00	0.84			
DSDD0124	496.00	497.00	1.00	0.94			
DSDD0124	497.00	498.00	1.00	0.93			
DSDD0124	498.00	499.00	1.00	0.88			
DSDD0124	499.00	500.00	1.00	0.37			
DSDD0124	500.00	501.00	1.00	0.23			
DSDD0124	501.00	502.00	1.00	0.40			
DSDD0124	502.00	503.00	1.00	0.55			
DSDD0124	503.00	504.00	1.00	0.51			
DSDD0124	504.00	505.00	1.00	0.36			
DSDD0124	505.00	506.00	1.00	<b>9.21</b>			
DSDD0124	506.00	507.00	1.00	0.60			
DSDD0124	507.00	508.00	1.00	0.90			<b>4 m @ 3.33 g/t Au</b>
DSDD0124	508.00	509.00	1.00	<b>2.60</b>			
DSDD0124	509.00	510.39	1.39	0.66			
DSDD0127	171.00	172.00	1.00	<b>1.77</b>	<b>1 m @ 1.77 g/t Au</b>	<b>1.8</b>	<b>1 m @ 1.77 g/t Au</b>
DSDD0127	257.00	258.00	1.00	0.20			
DSDD0127	258.00	259.00	1.00	0.20			
DSDD0127	259.00	260.00	1.00	<b>2.67</b>			
DSDD0127	260.00	261.00	1.00	<b>2.44</b>	<b>6 m @ 1.26 g/t Au</b>	<b>7.6</b>	<b>3 m @ 2.16 g/t Au</b>
DSDD0127	261.00	262.00	1.00	<b>1.38</b>			
DSDD0127	262.00	263.00	1.00	0.70			
DSDD0127	267.00	268.00	1.00	0.49			
DSDD0127	268.00	269.00	1.00	0.05			
DSDD0127	269.00	270.00	1.00	0.34			
DSDD0127	270.00	271.00	1.00	0.51			
DSDD0127	271.00	272.00	1.00	<b>2.30</b>			
DSDD0127	272.00	273.00	1.00	<b>1.81</b>			<b>2 m @ 2.06 g/t Au</b>
DSDD0127	273.00	274.00	1.00	0.80			
DSDD0127	274.00	275.00	1.00	0.86	<b>22 m @ 0.84 g/t Au</b>	<b>18.5</b>	
DSDD0127	275.00	276.00	1.00	0.75			
DSDD0127	276.00	277.00	1.00	<b>1.05</b>			
DSDD0127	277.00	278.00	1.00	<b>1.30</b>			
DSDD0127	278.00	279.00	1.00	0.19			
DSDD0127	279.00	280.00	1.00	<b>1.50</b>			
DSDD0127	280.00	281.00	1.00	<b>3.35</b>			<b>5 m @ 1.48 g/t Au</b>

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0127	281.00	282.00	1.00	0.62			
DSDD0127	282.00	283.00	1.00	0.64			
DSDD0127	283.00	284.00	1.00	0.26			
DSDD0127	284.00	285.00	1.00	0.29			
DSDD0127	285.00	286.00	1.00	0.27			
DSDD0127	286.00	287.00	1.00	0.50			
DSDD0127	287.00	288.00	1.00	0.38			
DSDD0127	288.00	289.00	1.00	0.27			
DSDD0127	312.00	313.00	1.00	0.25			
DSDD0127	313.00	314.00	1.00	0.13			
DSDD0127	314.00	315.00	1.00	0.16	4 m @ 0.24 g/t Au	1.0	
DSDD0127	315.00	316.00	1.00	0.44			
DSDD0127	321.00	322.00	1.00	<b>1.17</b>	1 m @ 1.17 g/t Au	1.2	<b>1 m @ 1.17 g/t Au</b>
DSDD0127	341.00	342.00	1.00	0.86			
DSDD0127	342.00	343.00	1.00	0.42			
DSDD0127	343.00	344.00	1.00	0.46	4.34 m @ 0.47 g/t Au	2.1	
DSDD0127	344.00	345.34	1.34	0.24			
DSDD0127	422.00	423.00	1.00	0.37			
DSDD0127	423.00	424.00	1.00	0.42			
DSDD0127	424.00	425.00	1.00	0.40			
DSDD0127	425.00	426.00	1.00	0.27			
DSDD0127	426.00	427.00	1.00	0.19	8 m @ 0.28 g/t Au	2.3	
DSDD0127	427.00	428.00	1.00	0.08			
DSDD0127	428.00	429.00	1.00	0.29			
DSDD0127	429.00	430.00	1.00	0.23			
DSDD0127	432.00	433.00	1.00	0.27			
DSDD0127	433.00	434.00	1.00	<b>1.06</b>			
DSDD0127	434.00	435.00	1.00	<b>1.24</b>			<b>2 m @ 1.15 g/t Au</b>
DSDD0127	435.00	436.00	1.00	0.17			
DSDD0127	436.00	437.00	1.00	0.31			
DSDD0127	437.00	438.00	1.00	0.71	11 m @ 0.48 g/t Au	5.3	
DSDD0127	438.00	439.00	1.00	0.20			
DSDD0127	439.00	440.00	1.00	0.21			
DSDD0127	440.00	441.00	1.00	0.10			
DSDD0127	441.00	442.00	1.00	0.35			
DSDD0127	442.00	443.00	1.00	0.70			
DSDD0127	451.00	452.00	1.00	0.49			
DSDD0127	452.00	453.00	1.00	0.36			
DSDD0127	453.00	454.00	1.00	0.27	14 m @ 0.40 g/t Au	5.5	
DSDD0127	454.00	455.00	1.00	0.71			
DSDD0127	455.00	456.00	1.00	0.27			



Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0127	456.00	457.00	1.00	0.46			
DSDD0127	457.00	458.00	1.00	0.74			
DSDD0127	458.00	459.00	1.00	0.08			
DSDD0127	459.00	460.00	1.00	0.40			
DSDD0127	460.00	461.00	1.00	0.12			
DSDD0127	461.00	462.00	1.00	0.74			
DSDD0127	462.00	463.00	1.00	0.13			
DSDD0127	463.00	464.44	1.44	0.45			
DSDD0127	464.44	465.00	0.56	0.20			
DSDD0127	470.00	471.00	1.00	0.54			
DSDD0127	471.00	472.00	1.00	0.01			
DSDD0127	472.00	473.00	1.00	<b>9.53</b>			
DSDD0127	473.00	474.00	1.00	<b>1.59</b>			
DSDD0127	474.00	475.00	1.00	<b>2.39</b>			
DSDD0127	475.00	476.00	1.00	0.87			
DSDD0127	476.00	477.00	1.00	0.93			
DSDD0127	477.00	478.00	1.00	<b>2.35</b>			
DSDD0127	478.00	479.00	1.00	<b>1.81</b>			
DSDD0127	479.00	480.00	1.00	<b>1.67</b>			
DSDD0127	480.00	481.00	1.00	0.09			
DSDD0127	481.00	482.00	1.00	0.48			
DSDD0127	482.00	483.00	1.00	0.27			
DSDD0127	483.00	484.00	1.00	0.33			
DSDD0127	484.00	485.00	1.00	0.30			
DSDD0127	506.00	507.00	1.00	0.73			
DSDD0127	507.00	508.00	1.00	0.71			
DSDD0127	508.00	509.00	1.00	0.29			
DSDD0127	510.00	511.00	1.00	0.59			
DSDD0127	511.00	512.00	1.00	0.20			
DSDD0127	512.00	513.00	1.00	0.18			
DSDD0127	513.00	514.00	1.00	0.56			
DSDD0127	514.00	515.00	1.00	0.70			
DSDD0127	515.00	516.00	1.00	<b>1.67</b>			
DSDD0127	516.00	517.00	1.00	0.58			
DSDD0127	517.00	518.00	1.00	0.94			
DSDD0127	518.00	519.00	1.00	0.43			
DSDD0127	519.00	520.00	1.00	0.80			
DSDD0127	520.00	521.00	1.00	0.10			
DSDD0127	521.00	522.00	1.00	0.11			
DSDD0127	522.00	523.00	1.00	0.26			
DSDD0127	523.00	524.00	1.00	0.33			
					<b>15 m @ 1.54 g/t Au</b>	<b>23.2</b>	<b>8 m @ 2.64 g/t Au</b>
					<b>3 m @ 0.58 g/t Au</b>	<b>1.7</b>	
					<b>15 m @ 0.51 g/t Au</b>	<b>7.7</b>	<b>1 m @ 1.67 g/t Au</b>

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0127	524.00	525.00	1.00	0.22			
DSDD0129	1.50	2.17	0.67	0.68	0.67 m @ 0.68 g/t Au	0.5	
DSDD0129	5.00	6.50	1.50	0.25	1.50 m @ 0.25 g/t Au	0.4	
DSDD0129	24.70	26.00	1.30	0.24	1.30 m @ 0.24 g/t Au	0.3	
DSDD0129	43.28	44.06	0.78	0.26	0.78 m @ 0.26 g/t Au	0.2	
DSDD0129	53.40	54.00	0.60	0.20	0.60 m @ 0.20 g/t Au	0.1	
DSDD0129	59.00	60.00	1.00	0.28			
DSDD0129	60.00	61.00	1.00	0.14	3 m @ 0.27 g/t Au	0.8	
DSDD0129	61.00	62.00	1.00	0.40			
DSDD0129	65.00	66.00	1.00	0.41	1 m @ 0.41 g/t Au	0.4	
DSDD0129	77.00	78.00	1.00	0.60	1 m @ 0.60 g/t Au	0.6	
DSDD0129	104.00	105.00	1.00	0.46	1 m @ 0.46 g/t Au	0.5	
DSDD0129	180.00	181.00	1.00	0.24			
DSDD0129	181.00	182.00	1.00	<b>1.41</b>	2 m @ 0.82 g/t Au	1.7	<b>1 m @ 1.41 g/t Au</b>
DSDD0129	189.00	190.00	1.00	<b>1.60</b>	1 m @ 1.60 g/t Au	1.6	<b>1 m @ 1.60 g/t Au</b>
DSDD0131	252.00	253.00	1.00	<b>1.33</b>			<b>1 m @ 1.33 g/t Au</b>
DSDD0131	253.00	254.00	1.00	0.83			
DSDD0131	254.00	255.00	1.00	0.35	6 m @ 0.52 g/t Au	3.1	
DSDD0131	255.00	256.00	1.00	0.11			
DSDD0131	256.00	257.00	1.00	0.01			
DSDD0131	257.00	258.00	1.00	0.49			
DSDD0131	259.00	260.00	1.00	0.56			
DSDD0131	260.00	261.00	1.00	0.11			
DSDD0131	261.00	262.00	1.00	0.02	6 m @ 0.37 g/t Au	2.2	
DSDD0131	262.00	263.00	1.00	0.03			
DSDD0131	263.00	264.00	1.00	<b>1.30</b>			<b>1 m @ 1.30 g/t Au</b>
DSDD0131	264.00	265.00	1.00	0.20			
DSDD0131	278.00	279.00	1.00	0.25			
DSDD0131	279.00	280.00	1.00	0.44			
DSDD0131	280.00	281.00	1.00	0.91	5 m @ 0.55 g/t Au	2.7	
DSDD0131	281.00	282.00	1.00	0.65			
DSDD0131	282.00	283.00	1.00	0.48			
DSDD0131	294.00	295.00	1.00	0.37			
DSDD0131	295.00	296.00	1.00	0.02			
DSDD0131	296.00	297.00	1.00	0.03			
DSDD0131	297.00	298.00	1.00	0.82	7 m @ 0.42 g/t Au	2.9	
DSDD0131	298.00	299.00	1.00	0.48			
DSDD0131	299.00	300.00	1.00	0.83			
DSDD0131	300.00	301.00	1.00	0.36			
DSDD0131	306.00	307.00	1.00	0.20	1 m @ 0.20 g/t Au	0.2	
DSDD0131	491.00	492.00	1.00	0.82	1 m @ 0.82 g/t Au	0.8	

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0131	496.00	497.00	1.00	0.43	1 m @ 0.43 g/t Au	0.4	
DSDD0131	501.00	502.00	1.00	0.27	12 m @ 0.41 g/t Au	4.9	
DSDD0131	502.00	503.00	1.00	0.13			
DSDD0131	503.00	504.00	1.00	0.49			
DSDD0131	504.00	505.00	1.00	0.15			
DSDD0131	505.00	506.00	1.00	0.22			
DSDD0131	506.00	507.00	1.00	0.89			
DSDD0131	507.00	508.00	1.00	0.78			
DSDD0131	508.00	509.00	1.00	0.43			
DSDD0131	509.00	510.00	1.00	0.38			
DSDD0131	510.00	511.00	1.00	0.36			
DSDD0131	511.00	512.00	1.00	0.14			
DSDD0131	512.00	513.00	1.00	0.66			
DSDD0131	537.29	538.00	0.71	0.33			6.71 m @ 0.23 g/t Au
DSDD0131	538.00	539.00	1.00	0.05			
DSDD0131	539.00	540.00	1.00	0.04			
DSDD0131	540.00	541.00	1.00	0.46			
DSDD0131	541.00	542.00	1.00	0.22			
DSDD0131	542.00	543.00	1.00	0.34			
DSDD0131	543.00	544.00	1.00	0.20			
DSDD0131	559.00	560.00	1.00	0.23	5 m @ 1.47 g/t Au	7.4	
DSDD0131	560.00	561.00	1.00	0.07			
DSDD0131	561.00	562.00	1.00	0.21			
DSDD0131	562.00	563.00	1.00	<b>4.18</b>			2 m @ 3.43 g/t Au
DSDD0131	563.00	564.00	1.00	<b>2.68</b>			
DSDD0131	565.00	566.00	1.00	0.20	7 m @ 1.16 g/t Au	8.1	
DSDD0131	566.00	567.00	1.00	0.08			
DSDD0131	567.00	568.00	1.00	<b>3.92</b>			1 m @ 3.92 g/t Au
DSDD0131	568.00	569.00	1.00	0.93			
DSDD0131	569.00	570.00	1.00	0.25			
DSDD0131	570.00	570.91	0.91	0.18			
DSDD0131	570.91	572.00	1.09	<b>2.38</b>			1.09 m @ 2.38 g/t Au
DSDD0131	589.53	591.00	1.47	0.48	14.47 m @ 0.57 g/t Au	8.2	
DSDD0131	591.00	592.00	1.00	0.16			
DSDD0131	592.00	593.00	1.00	<b>1.19</b>			1 m @ 1.19 g/t Au
DSDD0131	593.00	594.00	1.00	0.23			
DSDD0131	594.00	595.00	1.00	0.46			
DSDD0131	595.00	596.00	1.00	0.40			
DSDD0131	596.00	597.00	1.00	0.37			
DSDD0131	597.00	597.76	0.76	0.22			
DSDD0131	597.76	599.00	1.24	0.29			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0131	599.00	599.60	0.60	0.08			
DSDD0131	599.60	601.00	1.40	0.64			
DSDD0131	601.00	602.00	1.00	<b>2.46</b>			<b>1 m @ 2.46 g/t Au</b>
DSDD0131	602.00	603.00	1.00	0.57			
DSDD0131	603.00	604.00	1.00	0.20			
DSDD0132	10.32	11.00	0.68	0.20	0.68 m @ 0.20 g/t Au	0.1	
DSDD0132	13.25	13.75	0.50	<b>1.25</b>	0.50 m @ 1.25 g/t Au	0.6	0.50 m @ 1.25 g/t Au
DSDD0132	65.00	66.00	1.00	0.24	1 m @ 0.24 g/t Au	0.2	
DSDD0132	83.00	84.00	1.00	<b>14.92</b>	<b>1 m @ 14.92 g/t Au</b>	<b>14.9</b>	<b>1 m @ 14.92 g/t Au</b>
DSDD0132	116.00	117.00	1.00	0.23	1 m @ 0.23 g/t Au	0.2	
DSDD0132	156.00	157.00	1.00	0.27			
DSDD0132	157.00	158.00	1.00	0.28			
DSDD0132	158.00	159.00	1.00	0.03	6 m @ 0.78 g/t Au	4.7	
DSDD0132	159.00	160.00	1.00	0.01			
DSDD0132	160.00	161.00	1.00	0.06			
DSDD0132	161.00	162.00	1.00	<b>4.05</b>			
DSDD0132	163.00	164.00	1.00	<b>6.24</b>			<b>3 m @ 3.44 g/t Au</b>
DSDD0132	164.00	165.00	1.00	0.13			
DSDD0132	165.00	166.00	1.00	0.63	5 m @ 1.46 g/t Au	7.3	
DSDD0132	166.00	167.00	1.00	0.09			
DSDD0132	167.00	168.00	1.00	0.20			
DSDD0132	172.00	173.00	1.00	0.36			
DSDD0132	173.00	174.00	1.00	0.01			
DSDD0132	174.00	175.00	1.00	0.26	5 m @ 0.27 g/t Au	1.3	
DSDD0132	175.00	176.00	1.00	0.13			
DSDD0132	176.00	177.00	1.00	0.57			
DSDD0132	185.00	186.00	1.00	0.31			
DSDD0132	186.00	187.00	1.00	<b>1.17</b>			<b>1 m @ 1.17 g/t Au</b>
DSDD0132	187.00	188.00	1.00	0.27	6 m @ 0.39 g/t Au	2.4	
DSDD0132	188.00	189.00	1.00	0.18			
DSDD0132	189.00	190.00	1.00	0.14			
DSDD0132	190.00	191.00	1.00	0.29			
DSDD0132	197.00	198.00	1.00	0.26	1 m @ 0.26 g/t Au	0.3	
DSDD0132	202.00	203.00	1.00	<b>1.93</b>			<b>1 m @ 1.93 g/t Au</b>
DSDD0132	203.00	204.00	1.00	0.59			
DSDD0132	204.00	205.00	1.00	0.16	5 m @ 0.79 g/t Au	4.0	
DSDD0132	205.00	206.00	1.00	0.14			
DSDD0132	206.00	207.00	1.00	<b>1.15</b>			<b>1 m @ 1.15 g/t Au</b>
DSDD0132	208.00	209.00	1.00	0.31			
DSDD0132	209.00	210.00	1.00	<b>1.04</b>	<b>11 m @ 1.07 g/t Au</b>	<b>11.8</b>	<b>1 m @ 1.04 g/t Au</b>
DSDD0132	210.00	211.00	1.00	0.20			

Hole ID	From	To	Interval	Au (ppm)	Sig Int > 0.2 g/t Au	m*g/t Au (gpm)	Sig Int >1 g/t Au
DSDD0132	211.00	212.00	1.00	0.44			
DSDD0132	212.00	213.00	1.00	0.16			
DSDD0132	213.00	214.00	1.00	<b>6.61</b>			<b>1 m @ 6.61 g/t Au</b>
DSDD0132	214.00	215.00	1.00	0.25			
DSDD0132	215.00	216.00	1.00	0.37			
DSDD0132	216.00	217.00	1.00	0.04			
DSDD0132	217.00	218.00	1.00	0.28			
DSDD0132	218.00	219.00	1.00	<b>2.09</b>			<b>1 m @ 2.09 g/t Au</b>
DSDD0132	223.00	224.00	1.00	0.96	1 m @ 0.96 g/t Au	1.0	
DSDD0132	225.00	226.00	1.00	0.33			
DSDD0132	226.00	227.00	1.00	0.03			
DSDD0132	227.00	228.00	1.00	0.14			
DSDD0132	228.00	229.00	1.00	0.12			
DSDD0132	229.00	230.00	1.00	0.50			
DSDD0132	230.00	231.00	1.00	0.78	8 m @ 0.43 g/t Au	3.5	
DSDD0132	231.00	232.00	1.00	0.66			
DSDD0132	232.00	233.00	1.00	0.89			
DSDD0132	246.00	247.00	1.00	<b>1.05</b>	1 m @ 1.05 g/t Au	1.1	<b>1 m @ 1.05 g/t Au</b>
DSDD0135	1.00	2.00	1.00	0.26	1 m @ 0.26 g/t Au	0.3	
DSDD0135	50.00	51.00	1.00	0.26			
DSDD0135	54.00	55.00	1.00	0.22			
DSDD0135	55.00	56.09	1.09	0.25	2.09 m @ 0.24 g/t Au	0.5	
DSDD0135	74.00	75.00	1.00	0.30	1 m @ 0.30 g/t Au	0.3	
DSDD0135	82.00	83.00	1.00	0.34			
DSDD0135	83.00	84.00	1.00	<b>1.25</b>	2 m @ 0.80 g/t Au	1.6	<b>1 m @ 1.25 g/t Au</b>
DSDD0135	131.00	132.00	1.00	0.20			
DSDD0135	132.00	133.00	1.00	0.27			
DSDD0135	133.00	134.00	1.00	0.48			
DSDD0135	134.00	135.00	1.00	0.77			
DSDD0135	135.00	136.00	1.00	0.17	8 m @ 0.32 g/t Au	2.6	
DSDD0135	136.00	137.00	1.00	0.37			
DSDD0135	137.00	138.00	1.00	0.13			
DSDD0135	138.00	139.00	1.00	0.20			
DSDD0135	149.00	150.00	1.00	0.39	1 m @ 0.39 g/t Au	0.4	
DSDD0135	156.00	157.00	1.00	0.20			
DSDD0135	157.00	158.00	1.00	0.17			
DSDD0135	158.00	159.00	1.00	0.45			
DSDD0135	159.00	160.00	1.00	0.32	5 m @ 0.65 g/t Au	3.3	
DSDD0135	160.00	161.00	1.00	<b>2.13</b>			<b>1 m @ 2.13 g/t Au</b>
DSDD0135	168.00	169.00	1.00	0.25			
DSDD0135	169.00	169.60	0.60	<b>2.19</b>	1.60 m @ 0.98 g/t Au	1.6	0.60 m @ 2.19 g/t Au



### About Aurum's Boundiali Gold Project

The Boundiali Gold Project is comprised of four neighbouring exploration tenements (Figure 2):

- 1) Boundiali Minex Tenement PR0893 ("**BM**"), 400km<sup>2</sup>, holder Minex West Africa, of which Aurum holds 80% interest through its fully owned subsidiary Plusor Global Pty Ltd ("Plusor").
- 2) Boundiali DS tenement PR808 ("**BD**"), 260km<sup>2</sup>, holder DS Resources Joint Venture Company, of which Aurum is 80% share capital owner through its fully owned subsidiary Plusor.
- 3) Boundiali South tenement PR414 ("**BST**"), 167.34km<sup>2</sup> is located directly south of Aurum's **BD** and **BM** tenement. The **BST** exploration tenement was renewed on 19<sup>th</sup> August 2024. Predictive Discovery Côte d'Ivoire SARL (89% owned by Turaco Gold Limited and 11% owned by Predictive Discovery Limited) agreed to sell 100% interest to Aurum, subject to Aurum obtaining a renewal of the Boundiali South tenement (or the granting of a replacement tenement) and being satisfied that the terms of the renewal (or replacement) do not restrict exploration or potential future mining rights, along with all required Government approvals.
- 4) Boundiali North tenement PR283 ("**BN**"), 208.87km<sup>2</sup>, under renewal, Aurum to earn up to 70% interest through its wholly owned subsidiary Plusor.

The Boundiali Gold Project is located within the same greenstone belt as Resolute's large Syama (11.5Moz) gold mine and Perseus' Sissingue (1.4 Moz) gold mine to the north and Montage Gold's 4.5Moz Koné project located to the south. Barrick's Tongon mine (5.0Moz) is located to the northeast (Figure 1).

### BM gold project JV

Plusor has earned 80% interest through drilling 8,000m and spending US\$2.5M accumulated exploration expenditure.

- Completed drilling 4,000m diamond holes to earn 30% interest
- Completed drilling a further 4,000m diamond holes to earn accumulated 51% interest
- Earned an accumulated 80% interest from spending exploration expenditure of US\$2.5M using a nominal diamond drilling cost of US\$140/m in calculation for expenditure commitment.
- 80-88% interest in future gold production company (Government gets 10% free carry from local partner):
  - 80% if local partner contributes 11% capex
  - 85% if local partner does not contribute capex – they go to 5% free carry
  - 88% if local partner sells us 3% of their interest they go to 2% free carry

### BD gold project JV

Plusor owns 80% interest acquired from DS Joint Venture Company's two shareholders:

- acquired 45% share capital of DS Joint Venture Company Sarl by paying US\$430,000 to DS Resources Sarl; and
- acquired 35% share capital of DS Joint Venture Company Sarl from Turaco Gold Ltd by drilling 3,500m diamond holes in Turaco's other gold projects in Cote D'Ivoire. This commitment has been completed.
- 80-88% interest in future gold production company (Government gets 10% free carry from local partner):
  - 80% if local partner contributes 11% capex
  - 85% if local partner does not contribute capex – they go to 5% free carry
  - 88% if local partner sells us 3% of their interest they go to 2% free carry

### BST gold project consideration and payment for the binding term sheet



- Purchase of the tenement is subject to Aurum obtaining a renewal of the **BST** tenement (or the granting of a replacement) and being satisfied that the terms of the renewal (or replacement permit) do not restrict exploration or potential future mining rights, along with required Government approvals
- Within 15 business days of the satisfaction (or waiver) of the conditions precedent above, the Seller will, by written notice to the Purchaser, elect to receive **one** of the following forms of consideration (**Election**):
  - (i) A\$800,000 in cash (**Cash Consideration**); or
  - (ii) If the 20-day volume weighted average trading price of Shares (**VWAP**) is:
    - *Less than or equal to A\$0.20 at the time of the Election, 5,000,000 fully paid ordinary shares in the Purchaser (Shares) (Consideration Shares 1); or*
    - *Greater than A\$0.20 at the time of the Election, Shares to a value of A\$1.2 million, as determined by dividing A\$1.2 million by the 20-day VWAP for the Shares (Consideration Shares 2)*
- 90% interest in future gold production company (Government get 10% free carry from our interest)

#### **BN gold project JV**

Aurum is earning interest through carrying out exploration to earn 70% interest in three stages:

- Stage 1: Aurum earns 35% interest by spending USD 1.2 million within 36 months of license grant
- Stage 2: Aurum earns 51% interest by spending USD 2.5 million within 60 months of license grant
- Stage 3: Aurum earns 70% interest upon completion of a pre-feasibility study on the tenement.
- Diamond drilling conducted by Aurum will be valued at US\$140 per meter for expenditure calculations
- Upon grant of a mining exploitation license, the ownership structure will be: Aurum (70%), GNRR (20%), Ivorian Government (10%)

Section 1 of the JORC Code, 2012 Edition – Table 1

Sampling Techniques and Data

Criteria	JORC Code explanation	Commentary
<b>Sampling techniques</b>	<ul style="list-style-type: none"> <li>Nature and quality of sampling (e.g. cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling.</li> <li>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</li> <li>Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information.</li> </ul>	<ul style="list-style-type: none"> <li>Samples were collected using diamond drilling techniques generally angled at 50° towards north-northwest to optimally intersect the mineralised zones.</li> <li>Diamond core was logged both for geological and mineralised structures as noted above. The core was then cut in half using a diamond brick cutting saw on 1m intervals. Typically the core was sampled to geological intervals as defined by the geologist within the even two metre sample intervals utilised. The right-hand side of the core was always submitted for analysis with the left side being stored in trays on site</li> <li>Sampling and QAQC procedures were carried out to industry standards.</li> <li>Sample preparation was completed by independent international accredited laboratory Intertek Minerals Ltd. Following cutting or splitting, the samples were bagged by the Client employees and then sent to the laboratory for preparation. These samples were subsequently sent to Ghana for analysis via 30g fire assay.</li> </ul>
<b>Drilling techniques</b>	<ul style="list-style-type: none"> <li>Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc).</li> </ul>	<ul style="list-style-type: none"> <li>Diamond drilling carried out with mostly NTW and some HQ sized equipment. PQ-size rods and casing were used at the top the holes to stabilise the collars although no samples were taken from the PQ size core.</li> </ul>
<b>Drill sample recovery</b>	<ul style="list-style-type: none"> <li>Method of recording and assessing core and chip sample recoveries and results assessed.</li> <li>Measures taken to maximise sample recovery and ensure representative nature of the samples.</li> <li>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</li> </ul>	<ul style="list-style-type: none"> <li>Diamond drilling core recoveries ranged between 85% and 100% for all holes with no significant issues noted.</li> </ul>
<b>Logging</b>	<ul style="list-style-type: none"> <li>Whether core and chip samples have been geologically and geotechnically</li> </ul>	<ul style="list-style-type: none"> <li>All holes were field logged by company geologists. Lithological, alteration and</li> </ul>



Criteria	JORC Code explanation	Commentary
	<p><i>logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</i></p> <ul style="list-style-type: none"> <li>• <i>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.</i></li> <li>• <i>The total length and percentage of the relevant intersections logged.</i></li> </ul>	<p><i>mineralogical nomenclature of the deposit as well as sulphide content were recorded. Metallurgical, Geotechnical and structural data has been recorded</i></p> <ul style="list-style-type: none"> <li>• <i>Photography and recovery measurements were carried out by assistants under a geologist's supervision.</i></li> <li>• <i>All drill holes were logged in full.</i></li> <li>• <i>Logging was qualitative and quantitative in nature.</i></li> </ul>
<p><b>Sub-sampling techniques and sample preparation</b></p>	<ul style="list-style-type: none"> <li>• <i>If core, whether cut or sawn and whether quarter, half or all core taken.</i></li> <li>• <i>If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.</i></li> <li>• <i>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</i></li> <li>• <i>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</i></li> <li>• <i>Measures taken to ensure that the sampling is representative of the in-situ material collected, including for instance results for field duplicate/second-half sampling.</i></li> <li>• <i>Whether sample sizes are appropriate to the grain size of the material being sampled.</i></li> </ul>	<ul style="list-style-type: none"> <li>• <i>NTW core cut in half using a core saw. Typically, the core was sampled to major geological intervals as defined by the geologist within the even two metre sample intervals utilised. All samples were collected from the same side of the core.</i></li> <li>• <i>Sample sizes are considered appropriate to correctly represent the moderately nuggetty gold mineralisation based on: the style of mineralisation, the thickness and consistency of the intersections, the sampling methodology and assay value ranges for Au.</i></li> <li>• <i>The 250gm sample is milled through an LM5 using a single puck to 90% &lt;75 micron</i></li> <li>• <i>Milled sample is homogenised through a matt roll with a 150gm routine sample collected using a spoon around the quadrants and sent to Ghana for analysis and the remaining 100gm kept at Intertek for checks.</i></li> <li>• <i>Field QC procedures involved the use of 2 types of certified reference materials (1 in 20) which is certified by Geostats Ltd,</i></li> <li>• <i>Primary RC duplicates: Generated from the first splitter off the rig and inserted 5% (1 in 20 samples). This sample is collected from a spear sample from the reject material of the primary split.</i></li> <li>• <i>Primary DD duplicate: Generated by cutting the remaining half core into a ¼ and sampled.</i></li> <li>• <i>Coarse blank samples: Inserted 1 in every 20 samples</i></li> <li>• <i>Laboratory Internal Duplicates and Standards</i></li> <li>• <i>Sample sizes are considered appropriate</i></li> </ul>

Criteria	JORC Code explanation	Commentary
		<i>to correctly represent the moderately nuggetty gold mineralisation based on: the style of mineralisation, the thickness and consistency of the intersections, the sampling methodology and assay value ranges for gold</i>
<b>Quality of assay data and laboratory tests</b>	<ul style="list-style-type: none"> <li>• <i>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</i></li> <li>• <i>For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</i></li> <li>• <i>Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias) and precision have been established.</i></li> </ul>	<ul style="list-style-type: none"> <li>• <i>The analytical techniques used 50 gram Fire Assay on 150g pulp samples. Aurum is investigating assaying for gold using Chryso<sup>TM</sup> PhotonAssay methodology . This uses a high-energy X-ray source that is used to irradiate large mineral samples, typically about 500g compared to the 50g of the fire assay. The X-rays induce short-lived changes in the structure of any gold nuclei present. As the excited gold nuclei return to their ground state, they emit a characteristic gamma-ray signature, the intensity of which is directly proportional to the concentration of gold. The penetrating nature of Chryso<sup>TM</sup> PhotonAssay provides much higher energy than those used in conventional X-ray fluorescence (XRF), which provides a true bulk analysis of the entire sample. Samples are presented into a fully automatic process where samples are irradiated, measured, data collection and reporting. Further work is ongoing to determine the suitability of this method.</i></li> <li>• <i>No geophysical tools were used to determine any element concentrations used for this report.</i></li> <li>• <i>Sample preparation checks for fineness were carried out by the laboratory as part of internal procedures to ensure the grind size of 2mm was being attained. Laboratory QAQC includes the use of internal standards using certified reference material, and pulp replicates. No anomalous assays were noted in information provided to the Client.</i></li> <li>• <i>The QAQC results confirm that acceptable levels of accuracy and precision have been established for the Classifications applied.</i></li> </ul>
<b>Verification of sampling and assaying</b>	<ul style="list-style-type: none"> <li>• <i>The verification of significant intersections by either independent or alternative company personnel.</i></li> <li>• <i>The use of twinned holes.</i></li> <li>• <i>Documentation of primary data, data</i></li> </ul>	<ul style="list-style-type: none"> <li>• <i>NA</i></li> <li>• <i>No holes have been twinned</i></li> <li>• <i>No adjustment to assay data</i></li> <li>• <i>Logging records were mostly registered in physical format and were input into a</i></li> </ul>

Criteria	JORC Code explanation	Commentary
	<p>entry procedures, data verification, data storage (physical and electronic) protocols.</p> <ul style="list-style-type: none"> <li>Discuss any adjustment to assay data.</li> </ul>	<p>digital format. The core photographs, collar coordinates and down the hole surveys were received in digital format.</p> <ul style="list-style-type: none"> <li>Assay values that were below detection limit were adjusted to equal half of the detection limit value. Un-sampled intervals were assumed to have no mineralisation and they were therefore set to blank in the database, however these are minimal.</li> </ul>
<b>Location of data points</b>	<ul style="list-style-type: none"> <li>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</li> <li>Specification of the grid system used.</li> <li>Quality and adequacy of topographic control.</li> </ul>	<ul style="list-style-type: none"> <li>DD collar positions were located using a handheld GPS with a location error of +/-3m.</li> <li>The datum employed is WGS84, Zone 29</li> </ul>
<b>Data spacing and distribution</b>	<ul style="list-style-type: none"> <li>Data spacing for reporting of Exploration Results.</li> <li>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</li> <li>Whether sample compositing has been applied.</li> </ul>	<ul style="list-style-type: none"> <li>Drillholes were completed on variable spacings and orientations.</li> <li>No judgement has yet been made by an independent qualified consultant on whether the drill density is sufficient to calculate a Mineral Resource.</li> <li>The samples were not composited prior to assay.</li> </ul>
<b>Orientation of data in relation to geological structure</b>	<ul style="list-style-type: none"> <li>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</li> <li>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</li> </ul>	<ul style="list-style-type: none"> <li>Drill holes were drilled approximately at right angles to the anticipated strike of the target geochemical anomaly and orthogonal to the interpreted mineralisation orientation.</li> </ul>
<b>Sample security</b>	<ul style="list-style-type: none"> <li>The measures taken to ensure sample security.</li> </ul>	<ul style="list-style-type: none"> <li>Chain of custody is managed by the Client's senior site geologists and geotechnicians. Samples are stored in a core shed at site and samples were delivered to the laboratory by client geologists. Client employees have no further involvement in the preparation or analysis of the samples.</li> </ul>
<b>Audits or reviews</b>	<ul style="list-style-type: none"> <li>The results of any audits or reviews of sampling techniques and data.</li> </ul>	<ul style="list-style-type: none"> <li>Aurum is reviewing the suitability of PhotonAssay to analyse for gold compared to fire assay. This work is ongoing.</li> </ul>

Section 2 of the JORC Code, 2012 Edition – Table 1

Criteria	JORC Code explanation	Commentary
<b>Mineral tenement and land tenure status</b>	<ul style="list-style-type: none"> <li>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</li> <li>The security of the tenure held at the time of reporting along with any known impediments to obtaining a license to operate in the area.</li> </ul>	<ul style="list-style-type: none"> <li>Exploration results are from the Boundiali project area.</li> <li>There are no impediments to working in the area.</li> </ul>
<b>Exploration done by other parties</b>	<ul style="list-style-type: none"> <li>Acknowledgment and appraisal of exploration by other parties.</li> </ul>	<ul style="list-style-type: none"> <li>The exploration results reported in this announcement are from work undertaken by PlusOr and BM on behalf of Aurum Resources Limited</li> <li>The license area is known as a prospective region for gold and recent artisanal workings revealed the presence of primary gold mineralisation in artisanal pits and small-scale underground mining.</li> </ul>
<b>Geology</b>	<ul style="list-style-type: none"> <li>Deposit type, geological setting and style of mineralisation.</li> </ul>	<ul style="list-style-type: none"> <li>The geology consists of granitoid intrusives, metasediments, typical of granite – greenstone belt Birimian terrains. Mineralisation style is typical structurally controlled, mesothermal, lode gold orogenic style.</li> </ul>
<b>Drill hole information</b>	<ul style="list-style-type: none"> <li>A summary of all information material to the under-standing of the exploration results including a tabulation of the following information for all Material drill holes: <ul style="list-style-type: none"> <li>easting and northing of the drill hole collar</li> <li>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</li> <li>dip and azimuth of the hole</li> <li>down hole length and interception depth</li> <li>hole length</li> </ul> </li> <li>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</li> </ul>	<ul style="list-style-type: none"> <li>Complete drill hole data has been provided.</li> <li>Drill hole collar locations are shown in figures in main body of announcement.</li> </ul>

Criteria	JORC Code explanation	Commentary
<b>Data aggregation methods</b>	<ul style="list-style-type: none"> <li>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.</li> <li>Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</li> <li>The assumptions used for any reporting of metal equivalent values should be clearly stated.</li> </ul>	<ul style="list-style-type: none"> <li>Assay Intervals are shown in detail. Drilling intervals are predominantly 1m and 2m.</li> <li>Metal equivalent values are not being reported.</li> </ul>
<b>Relationship between mineralisation widths and intercept lengths</b>	<ul style="list-style-type: none"> <li>These relationships are particularly important in the reporting of Exploration Results.</li> <li>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</li> <li>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known').</li> </ul>	<ul style="list-style-type: none"> <li>True widths have not been estimated as the geological controls on mineralisation in these initial drill holes into the prospect are not yet well understood.</li> <li>The holes were drilled from east to west to test a steeply east dipping foliation in the limited rock exposures seen in the area. The mineralisation lies within what has been interpreted to be a ductile shear zone which would suggest that mineralisation should lie parallel to foliation.</li> </ul>
<b>Diagrams</b>	<ul style="list-style-type: none"> <li>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</li> </ul>	<ul style="list-style-type: none"> <li>Appropriate diagrams relevant to material results are shown in the body of this announcement.</li> </ul>
<b>Balanced Reporting</b>	<ul style="list-style-type: none"> <li>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</li> <li>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</li> </ul>	<ul style="list-style-type: none"> <li>All drill hole and trench collar locations were surveyed utilising handheld GPS methods. Exploration results only being reported. No Mineral Resource exists</li> <li>Drilling teams utilised the Reflex EZ-shot instrument to measure deviations in azimuth and inclination angles for all holes; however, vertical holes were not surveyed. The first measurement is taken at 6 m depth, and then at approximately every 30m depth interval and at the end of the hole. being reported</li> </ul>

Criteria	JORC Code explanation	Commentary
<b>Other substantive exploration data</b>	<ul style="list-style-type: none"> <li>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples - size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</li> </ul>	<ul style="list-style-type: none"> <li>All relevant exploration data is either reported in this announcement or has been reported previously by Aurum, Randgold or Predictive Discovery and is referred to in the announcement.</li> </ul>
<b>Further work</b>	<ul style="list-style-type: none"> <li>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large- scale step-out drilling).</li> <li>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</li> </ul>	<ul style="list-style-type: none"> <li>The Company intends to continue exploration on the project and this work will include auger, aircore, RC and diamond core drilling, along with further geophysical surveys and geochemical sampling programs.</li> <li>Diagrams included in body of report as deemed appropriate by competent person</li> </ul>